

GLOBAL JOURNAL OF RESEARCHES IN ENGINEERING: G INDUSTRIAL ENGINEERING Volume 23 Issue 2 Version 1.0 Year 2023 Type: Double Blind Peer Reviewed International Research Journal Publisher: Global Journals Online ISSN: 2249-4596 & Print ISSN: 0975-5861

Modeling and Optimization of Corrosion Penetration Rate in Crude Oil Pipeline using Response Surface Methodology based on Aspen HYSYS Simulation Software

By Sulayman H. Ameitiq & Omar M. Aldenali

University of Benghazi/ Libya

Abstract- This study aims to investigate the influence of a number of related parameters namely temperature, pressure, flow rate and pH on the corrosion penetration rate (CPR) of crude oil transportation process by pipelines. It intends the mathematical model of these parameters as independent variables with corrosion penetration rate as a dependent variable. The model was used to establish the best values of these parameters using the response surface methodology. Aspen HYSYS software was utilized to simulate the experiments and to calculate the corrosion penetration rate for each experiment. The experiments designed based on the central composite experimental design (CCD) using Minitab 17 software. The mean absolute percentage error was used to determine the conformance of the developed mathematical model. Its value was 0.02%, this indicates that the developed mathematical model was consistent.

Keywords: corrosion penetration rate (CPR), aspen hysys, response surface methodology (RSM), modeling, optimization.

GJMR-G Classification: LCC: TN879.5.P55

MODELLINGANOD PTIMIZATI OND FORROSI ON PENETRATI ON KATE IN DRUDED I LPI PELINEUSI NDREEPONSE SUR FADEMETRODOLOGV BASE DONASPENNYSYSI MULATI ONSO FTWARE

Strictly as per the compliance and regulations of:



© 2023. Sulayman H. Ameitiq & Omar M. Aldenali. This research/review article is distributed under the terms of the Attribution-NonCommercial-NoDerivatives 4.0 International (CC BY-NC-ND 4.0). You must give appropriate credit to authors and reference this article if parts of the article are reproduced in any manner. Applicable licensing terms are at https://creativecommons.org/licenses/by-nc-nd/4.0/.

Modeling and Optimization of Corrosion Penetration Rate in Crude Oil Pipeline using Response Surface Methodology based on Aspen HYSYS Simulation Software

Sulayman H. Ameitiq ^a & Omar M. Aldenali ^o

Abstract- This study aims to investigate the influence of a number of related parameters namely temperature, pressure, flow rate and pH on the corrosion penetration rate (CPR) of crude oil transportation process by pipelines. It intends the mathematical model of these parameters as independent variables with corrosion penetration rate as a dependent variable. The model was used to establish the best values of these parameters using the response surface methodology. Aspen HYSYS software was utilized to simulate the experiments and to calculate the corrosion penetration rate for each experiment. The experiments designed based on the central composite experimental design (CCD) using Minitab 17 software. The mean absolute percentage error was used to determine the conformance of the developed mathematical model. Its value was 0.02%, this indicates that the developed mathematical model was consistent. The Nash Sutcliffe efficiency (NSE) was also calculated. Its value was 0.999 which confirms the high-efficiency of the model. The optimal corrosion penetration rate conditions were determined. temperature (100°F), pressure (360 psig), flow rate (150,000 bbl/day), and pH (5.65). Accordingly, the minimum corrosion penetration rate is (3.98 mm/year).

Keywords: corrosion penetration rate (CPR), aspen hysys, response surface methodology (RSM), modeling, optimization.

I. INTRODUCTION

orrosion has a very important economy impact in the oil and gas industry. Oilfield production environments can range from practically zero corrosion to extremely high rates corrosion. The most predominant form of corrosion encountered in oil and gas production is the one caused by CO2. Dissolved carbon dioxide in the produced brines is very corrosive to carbon and low alloy steel tubular and to process equipment used in this industry. The costs of corrosion control are significant and are mainly related to materials replacement and corrosion control programs. Approximately 60% of oilfield failures are related to CO2 corrosion mainly due inadequate to

knowledge/predictive capability and the poor resistance of carbon and low alloy steels to this type of corrosive attack. CO2 can cause not only general corrosion but also localized corrosion, which is a much more serious problem [1, 3].

Pipelines whether buried in the ground, exposed to the atmosphere, or submerged in water, are liable to corrosion. Without proper maintenance, every pipeline system will eventually deteriorate, and a corroded pipe is unsafe as a means of transportation because of the associated failure risks. These failures in pipelines and flow lines lead to shutdown of facilities and platforms. Corrosion results in the deterioration of a metal and weakens its structural integrity as a result of chemical reactions between it and the surrounding environment [2]. Corrosion in pipelines occurs where there is loss of metal from an exposed surface in a corrosive environment. The majority of pipeline failures are caused by localized corrosion, and its mechanism can be induced by flow, metallurgy, deposits, internal stresses, and microbiologically influenced corrosion (MIC) among others. The internal corrosion of carbon steel is a noteworthy problem for the oil and gas industry because of its frequency of occurrence. Although high cost corrosion resistant alloys (CRAs) are often developed to resist internal corrosion, carbon steel is still the most cost effective material used for oil and gas production. Issues of possible corrosive species encountered in the oil and gas industry have been documented in so many literatures. The reports on the significance of CO2 in corrosion of metal have also been reported; and, there seems to be a consensus on the significance of CO2 in corrosion of flow lines [2]. Corrosion control is an ongoing dynamic process; therefore, an effective model for predicting pipeline corrosion is essential. Corrosion models give early caution signs of impending failures; they are developed correlations that relate processes and their corrosive effects on systems which help to diagnose a specific problem and in turn evaluate the effectiveness of any corrosion control measure/prevention technique applied to improve the service life of the target metal [2].

Author α: Faculty of Engineering University of Benghazi/ Libya. e-mail:sulayman.ameitiq@uob.edu.ly

Author o: Faculty of Engineering Libyan International Medical University. e-mail: omar.aldenali@limu.edu.ly

Corrosion has been one of the primary mechanisms causing failures of infrastructure in the oil and gas industry. The corrosion phenomenon can be found in all stages of oil production and transportation and processing. In addition to downhole tubulars, corrosion has been a vital threat to integrity of the above-ground pipelines [4].

II. LITERATURE REVIEW

Aspen HYSYS software for on-site simulation research was used to analyze the corrosion rate in the collection pipeline and to predict CO2 corrosion in the natural gas pipeline system. Different models were employed to estimate the CO2 corrosion such as NORSOK standard M-506, and De Waard model 1991 and 1995. The study's goal was to look at the influence of operating circumstances, inhibitors, pipe characteristics, and flow system on CO2 corrosion. When the working pressure is more than 10 MPa and the solution contains 0.85 kmol/m3 of iron carbonate, raising the operating pressure causes a rise in pH and a drop in CO2 corrosion rate. By comparing the data of simulation with field corrosion rate data, the feasibility of the numerical simulation method was proved [3].

Carbon dioxide corrosion in natural gas collection pipelines was predicted through the use of Aspen HYSYS simulation software and the effect of operating pressure, temperature, pH solution, pipeline length, flow regime, and pipe inclination on the CO2 was examined. The findings showed that raising the operating pressure raises the partial pressure of carbon dioxide and accelerates corrosion. The temperature influences the formation of the protective layer, as the maximum rate of carbon dioxide corrosion is 2.96 mm/year at 40 °C. As the concentration of dissolved carbon dioxide decreases along the pipeline, so does the corrosion rate. High speed results in effective confusion, preventing the formation of the protective layer and increasing carbon dioxide erosion [5].

The effect of many operational events (temperature, partial pressure of carbon dioxide, flow rate, and acidity) in the erosion of oil and gas lights was studied. A multi –lines slope was used to examine field data from wild oil and gas fields to assess the rate of corrosion dependence on operational transactions. ANOVA, P value test, and multiple regression coefficients were used in statistical analysis of data, while previous experimental results used De Waaard-Milliams models and the De Waaard-LOTZ model to verify exceptional well erosion rates. According to the survey, operational transactions represent about 26 % of the deterioration of wells. The expected corrosion models were also compatible with field data and Dideaard-Lotz models [6].

To estimate the rate of carbon steel corrosion, the response surface methodology (RSM) was utilized.

Response surface methodology (RSM), a form of statistical model, has demonstrated a successful way for decreasing the number of runs. The influence of the pH, CO2 pressure and temperature on corrosion rate of carbon steel were considered. The NORSOK corrosion software with the second order model has 98 % of coefficient determination. Moreover, the results show that the second-order model was confirmed using experimental data, indicating an excellent correlation [7].

Response surface methodology (RSM) was employed to study, model, and optimize the effect of some operation parameters of crude oil transportation processes, by pipeline, on the corrosion penetration rate (CPR). The parameters pressure, temperature, and pH were studied, and their ranges were determined. The predicted values obtained using the developed model were compared with the actual values calculated using NORSOK M-506 standard software based on the mean absolute error(MAE). The value of the MAE was 0.047467 which indicated that the model was reliable and significant [8].

The influence of many operational parameters (temperature, pressure, shear stress, and pH) were analyzed on the corrosion penetration rate, and optimal values of process parameters were determined. The response surface methodology (RSM) and fuzzy logic (FL) were used to predict the corrosion penetration rate that occurs during the process of transporting crude oil through the pipeline. The optimum values of operating conditions were the temperature is 44.4 ° C, the pressure is 34.28 Pascal, pH is 5.51 and the shear stress is 1 bar to achieve the lowest CPR of 2.16 mm/year [9].

It is considered that the Aspen HYSYS software can simulate the transportation of oil and gas through pipelines and produce results that are extremely close to reality. Response surface methodology is used for modeling and analysis.

This study aims to simulate crude oil transporting pipelines using the Aspen HYSYS software, afterwards design experiments using (RSM) and applying them through simulation, then using the results to create a model to predict corrosion penetration rate inside the pipeline and identifying the most suitable values for operating conditions.

III. MATERIALS AND METHODS

a) Material

Many elements influence CPR. The influence of the factors temperature, pressure, flow rate, and pH on the corrosion penetration rate was investigated in this study utilizing RSM.

The pipeline considered in this study is according to AGOCO from the Sarir field to Hrayqa oil port in Tobruk, the entire distance of pipeline is 514 km, pipeline diameter 34 inch, and mole percent of CO2 was set at 0.8% for the period between 01/01/2019 and operational param 01/01/2023 for oil pipeline. Table 1 shows the field over the period

operational parameters and related ranges in the Sarir field over the period.

No.	Daramatara	Notation	Unit	Range		
	1 arameters	INOLALIOII		Lower value	Upper value	
1	Temperature (°F)	Т	°F	100	130	
2	Pressure (psig)	Р	psig	360	580	
3	Flow Rate (bbl/day)	FR	bbl/day	150,000	240,000	
4	pН	pН	-	5.51	5.65	

Table 1: Experimental Ranges in Terms of Uncertain Parameters

b) Method

In this work, the variables considered are those most critical to CPR; temperature, pressure, flow rate, and pH. The experimental design was conducted according to the CCD method in Minitab 17 program for four factors and one response. CCD determined total experimental runs of 31 as shown in Table 2. To carry out these experiments, the reality was simulated using Aspen HYSYS V10 by creating a 514 km pipeline, filled with the chemical composition of raw oil, and calculating the corrosion penetration rate using the De Waard 1995 method, as shown in Figure 1.



Fig. 1: Simulation of the Oil Pipeline using Aspen HYSYS

Run Order	Temperature (°F)	Pressure (psig)	Flow Rate (bbl/day)	pН
1	115	470	240,000	5.58
2	115	470	195,000	5.58
3	115	360	195,000	5.58
4	100	360	240,000	5.65
5	115	580	195,000	5.58
6	130	360	240,000	5.65
7	115	470	195,000	5.51
8	130	360	150,000	5.51
9	115	470	195,000	5.58
10	115	470	195,000	5.58
11	100	580	150,000	5.65
12	100	360	150,000	5.51
13	100	470	195,000	5.58
14	100	580	240,000	5.51
15	115	470	195,000	5.58
16	100	360	150,000	5.65
17	130	580	150,000	5.51

Table 2: Design	of Experiment	and its Actual	Values of CPF
-----------------	---------------	----------------	---------------

Year 2023

Modeling and Optimization of Corrosion Penetration Rate in Crude Oil Pipeline using Response Surface Methodology based on Aspen HYSYS Simulation Software

18	100	580	150,000	5.51
19	100	580	240,000	5.65
20	130	360	150,000	5.65
21	130	580	150,000	5.65
22	100	360	240,000	5.51
23	115	470	195,000	5.58
24	130	470	195,000	5.58
25	130	580	240,000	5.65
26	115	470	150,000	5.58
27	115	470	195,000	5.58
28	130	360	240,000	5.51
29	130	580	240,000	5.51
30	115	470	195,000	5.58
31	115	470	195,000	5.65

IV. Discussion of Results and Optimization

Minitab worksheet, and after that the predicted values of CPR were calculated as shown in Table 3.

a) Results

The response data were calculated by the Aspen HYSYS model. Then, the data were entered in the

Tables 3: Actual Values by Aspen HYSYS Model and Predicted Values by RSM

Run Order	Temperature (°F)	Pressure (psig)	Flow Rate (bbl/day)	pН	Actual CPR (mm/year)	Predicted CPR (mm/year)
1	115	470	240,000	5.58	5.6578	5.6555
2	115	470	195,000	5.58	5.1139	5.1161
3	115	360	195,000	5.58	5.0475	5.0397
4	100	360	240,000	5.65	4.8703	4.8502
5	115	580	195,000	5.58	5.0855	5.0883
6	130	360	240,000	5.65	6.0183	6.0394
7	115	470	195,000	5.51	5.2187	5.2129
8	130	360	150,000	5.51	4.8189	4.8133
9	115	470	195,000	5.58	5.1139	5.1161
10	115	470	195,000	5.58	5.1139	5.1161
11	100	580	150,000	5.65	4.1568	4.1357
12	100	360	150,000	5.51	4.1388	4.1472
13	100	470	195,000	5.58	4.6811	4.7307
14	100	580	240,000	5.51	5.3160	5.3243
15	115	470	195,000	5.58	5.1139	5.1161
16	100	360	150,000	5.65	3.9784	3.9871
17	130	580	150,000	5.51	4.6784	4.6993
18	100	580	150,000	5.51	4.3237	4.3030
19	100	580	240,000	5.65	5.0553	5.0613
20	130	360	150,000	5.65	4.6749	4.6675



21	130	580	150,000	5.65	4.5270	4.5465
22	100	360	240,000	5.51	5.1253	5.1061
23	115	470	195,000	5.58	5.1139	5.1161
24	130	470	195,000	5.58	5.5782	5.5235
25	130	580	240,000	5.65	5.9883	5.9808
26	115	470	150,000	5.58	4.4618	4.4590
27	115	470	195,000	5.58	5.1139	5.1161
28	130	360	240,000	5.51	6.2590	6.2809
29	130	580	240,000	5.51	6.2377	6.2294
30	115	470	195,000	5.58	5.1139	5.1161
31	115	470	195,000	5.65	5.0077	5.0085

Table 4 shows the p-values that determine whether the effects are significant or insignificant.

Table 4: Estimated Regression Coefficient for CPR (mm/year)

Term	Effect	Coef	SE Coef	p-Value	
Constant		5.11609	0.00721	0.000	Significant
Temperature (°F)	0.79277	0.39639	0.00573	0.000	Significant
Pressure (psig)	0.04859	0.0243	0.00573	0.001	Significant
Flow Rate (bbl/day)	1.19657	0.59829	0.00573	0.000	Significant
pH	-0.20439	-0.10219	0.00573	0.000	Significant
Temperature (°F)*Temperature (°F)	0.022	0.011	0.0151	0.476	Insignificant
Pressure (psig)*Pressure (psig)	-0.1042	-0.0521	0.0151	0.003	Significant
Flow Rate (bbl/day)*Flow Rate (bbl/day)	-0.1176	-0.0588	0.0151	0.001	Significant
pH*pH	-0.0109	-0.0054	0.0151	0.724	Insignificant
Temperature (°F) *Pressure (psig)	-0.13484	-0.06742	0.00608	0.000	Significant
Temperature (°F) *Flow Rate	0.25436	0.12718	0.00608	0.000	Significant
Temperature (°F) *pH	0.00721	0.00361	0.00608	0.561	Insignificant
Pressure (psig)*Flow Rate (bbl/day)	0.0312	0.0156	0.00608	0.021	Significant
Pressure (psig)*pH	-0.00353	-0.00177	0.00608	0.775	Insignificant
Flow Rate (bbl/day)*pH	-0.04789	-0.02395	0.00608	0.001	Significant

The equation from table of estimated regression coefficients for corrosion penetration rate (mm/year) of the first – second order is given as *equation 1:*

CPR = -32.7 - 0.0215 T + 0.00963 P + 0.000044 FR + 12.1 pH + 0.000049 T*T - 0.000004 P*P- 0.000000 FR*FR-1.11 pH*pH - 0.000041 T*P + 0.000000 T*FR + 0.00344 T*pH + 0.000000 P*FR - 0.000230 P*pH - 0.000008 FR*pH (1) where: CPR: Corrosion Penetration Rate (mm/year) T: Temperature (°F) P: Pressure (psig)

FR: Flow Rate (bbl/day)

рН: -

Table 4 shows that all p-values associated with each individual model term. The terms are significant when alpha value is < 0.05.

b) Model Validation

To validate the developed model, the mean absolute percentage error (MAPE) was used to estimate the variation between the actual and predicted CPR. The value of the MAPE is 0.02%, compared with the actual values of Corrosion Penetration Rate, as plotted in Figure 2. The Nash-Sutcliffe Efficiency (NSE) was calculated for the model by Eq.2. The value of the NSE is 0.999, which indicates that the model is very good.

NSE =
$$1 - \frac{\sum (A - P)^2}{\sum (A - \hat{A})^2}$$
 (2)

Where:

A: Actual value for CPR.

Â: Average actual value for CPR.

P: Predicted value for CPR.



Fig. 2: The Actual and the Predicted Corrosion Penetration Rate

In addition, a probability plot is also used to identify the appropriate distribution. The Normal probability plot has some points that do not lie along the line in the upper and lower region. This may indicate potential outliers in data. Various fits, histograms, and order distributions are shown in Figure 3. It can be seen from the probability plots, that the data are from a normal distribution is the best one since all data fall within the 95% confidence interval.



Fig. 3: Probability Plots for Corrosion Penetration Rate

Optimization of Corrosion Penetration Rate C)

As can be indicated from Figure 4, for a simulation model of one year, the minimum corrosion penetration rate conditions were determined as,

temperature (100 °F), pressure (360 psig), flow rate (150,000 bbl/day), and pH (5.65). Accordingly, the minimum corrosion penetration rate is 3.98 mm/year.



Fig. 4: Main Effect Plots of Crude Oil CPR Processes Parameters Temperature, Pressure, Flow Rate and pH

Figure 5 illustrates the contour plots that represent the simultaneous effect of two variables on response, with the other variables fixed to the mean value in the range of factors. As the stronger the effect, the color in the drawing is green, and the weaker the effect, the color is blue. As an illustration, this figure shows a contour plot that represents the simultaneous effect of flow rate and temperature at pressure=480 and pH=5.58 on CPR, the larger values of the factors (flow rate 240,000 bbl/day and temperature 130 °F) giving the greater value of the corrosion penetration rate, and the smaller values of the factors (flow rate 150,000 bbl/day and temperature 100 °F) giving the lower value of the corrosion penetration rate.



Fig. 5: Contour Plots

V. Conclusions

In this study, attempts were made to predict the corrosion penetration rate of the pipelines that are used for transporting crude oil between Sarir-Tobruk stations. The corrosion penetration rate values were determined by using Aspen HYSYS V10 software.

The following points summarize the conclusions of the study:

- 1. Based on ANOVA analysis, the four factors considered had significant effects on the corrosion penetration rate, as well as the quadratic effect for pressure and flow rate were significant, while temperature and pH were insignificant. However, the interaction between (temperature and pH), and (pressure and pH) had no significant effect on corrosion penetration rate. Also the interaction between (temperature and pressure), (temperature and flow rate), (pressure and flow rate), and (flow rate and pH) had significant effects.
- 2. Based on the comparison between the actual values of corrosion penetration rate calculated by using Aspen HYSYS software and the predicted values of corrosion penetration rate by using the RSM technique, it can be concluded that the RSM model could be used to predict the values of corrosion penetration rate, under the specified parameters ranges, with a mean absolute percentage error of 0.02%.
- The optimal value for the numerically calculated corrosion penetration rate using the RSM model, was found to be 3.98 mm/year, with operating parameters values of temperature (100 °F), pressure (360 psig), flow rate (150,000 bbl/day), and pH (5.65).

Acknowledgments

The authors would like to thank the engineers at the Arabian Gulf Oil Company's Corrosion Department for giving the data and allowing them to publish the research.

References Références Referencias

- Kermani, M., and Smith, L., "CO2 corrosion control in the oil and gas production design considerations", European Federation of Corrosion, 1997.
- 2. Okoro, E., and et al., "Flow line corrosion failure as a function of operating temperature and CO2 partial pressure using real time field data", Engineering Failure Analysis, pp 160-169, 2019.
- 3. Dai, M., "In situ mathematically simulation for CO2 internal corrosion in wet natural gas gathering pipelines system by HYSYS", Engineering Failure Analysis, Vol. 122, 2021.
- 4. Tang, X., Richter, S., and Nesic, S., "An improved model for water wetting prediction in oil-water two-phase flow", Corrosion 2013, NACE International, 2013.
- 5. Abd, A.A., Naji, S.Z. and Hashim, A.S., "Failure analysis of carbon dioxide corrosion through wet natural gas gathering pipelines", Engineering Failure Analysis, pp 638-646, 2019.
- 6. Ossai, C.I., "Predictive modelling of wellhead corrosion due to operating conditions: a field data approach", International Scholarly Research Notices, 2012.
- 7. Asmara, Y.P., Sutjipto, A.G.E., Kurniawan, J.T. and Siregar, J.J.P., "Analyses corrosion prediction software for co2 corrosion of carbon steel using statistical formulas", International Journal of

© 2023 Global Journals

Mechanical Engineering and Robotics Research, Vol. 8(3), pp 374-379, 2019.

- Lahrash, M., "Optimizing Crude Oil in Transportation Pipeline using Response Surface Methodology", M.Sc. Thesis, Eastern Mediterranean University, Turkey, September 2017.
- Elrifai, A., R., "Modelling and optimization of corrosion penetration rate (CPR) for crude oil transportation processes by pipeline", M.Sc. Thesis, University of Surface Methodology",