Artificial Intelligence formulated this projection for compatibility purposes from the original article published at Global Journals. However, this technology is currently in beta. *Therefore, kindly ignore odd layouts, missed formulae, text, tables, or figures.*

On the Diffusion Mechanism in Melts of Condensation and Non-Condensation Polymers at High Temperatures

Stoyko Fakirov

Received: 12 April 2021 Accepted: 30 April 2021 Published: 15 May 2021

6 Abstract

1

2

3

4

7 As recently assumed (DOI:10.3144/expresspoly mlett.2019.25), the diffusion mechanism in

⁸ melts of noncondensation and condensation polymers at high temperatures must be rather

9 different due to the intensive exchange (trans) reactions resulting in dissipation of

¹⁰ condensation macromolecules into single repeating units. Considering these peculiarities of

¹¹ condensation polymers, it is concluded that the Reptation concept can be used for explaining

¹² the diffusion mechanism of non-condensation polymers (e. g. polyolefins) in the entire

¹³ temperature interval while for condensation polymers it is applicable only in the range

¹⁴ between Tm and approximately (Tm +100)°C. At much higher temperatures, where the

¹⁵ exchange reactions are extremely intensive, the diffusion mechanism seems to be the same as

¹⁶ in the case of low molecular weight substances.

17

18 Index terms— diffusion mechanism; condensation polymers; exchange- (trans) reactions; reptation model.

¹⁹ 1 Introduction

iffusion is a physical process that refers to the net movement of molecules from a region of high concentration to one of lower concentration. The material that diffuses could be a solid, liquid or gas. In the case of solids some additional requirements are needed -the temperature must be above the melting temperature of the respective crystals or above the glass transition temperature of amorphous solids.

²⁴ 2 a) The diffusion mechanism in low molecular weight sub stances

The diffusion process in low molecular weight substances is well studied. Its basic characteristic feature is that independent kinetic entities are the whole molecules, that is, the whole molecules move but not parts of them only. The mass transfer could be represented as a process consisting of "jump-like" steps.

Let remind the picture of diffusion and flow in the case of low molecular weight liquids. If molecules have 29 spherical shape, and they are densely packed, between the spheres (A) there are empty places (B), as shown in 30 Figure 1. According to the ideas of Frenkel [1] the molecules vibrate with a given frequency. At some of vibrations 31 the molecule "jump" in the neighboring empty place (e.g. A? B, Figure 1). After several vibrations around the 32 new equilibrium state with the same frequency, the molecule "jump" again into another empty place. In this 33 way is realized the process of selfdiffusion of liquid molecules expressed in displacement of center of gravity of 34 35 molecules, i.e. a flow takes place. Abstract-As recently assumed (DOI:10.3144/expresspoly mlett.2019.25), the 36 diffusion mechanism in melts of noncondensation and condensation polymers at high temperatures must be rather 37 different due to the intensive exchange (trans) reactions resulting in dissipation of condensation macromolecules into single repeating units. Considering these peculiarities of condensation polymers, it is concluded that the 38 Reptation concept can be used for explaining the diffusion mechanism of non-condensation polymers (e. g. 39 polyolefins) in the entire temperature interval while for condensation polymers it is applicable only in the range 40 between Tm and approximately $(Tm + 100)^{\circ}C$. At much higher temperatures, where the exchange reactions 41 are extremely intensive, the diffusion mechanism seems to be the same as in the case of low molecular weight 42

43 substances.

The experimental data regarding the frequency of exchange reactions in melts of condensation polymers show at least 10 reactions in a minute in one macromolecule (at low melt temperatures) and more than 100 reactions, but in a second (at high melt temperatures). At such temperature, the single independent kinetic elements are short fragments of macromolecules, and the diffusion mechanism in melts of condensation polymers seems to be the same, as that in the low molecular weight substances.

$_{49}$ 3 b) The diffusion mechanism in high molecular weight sub- $_{50}$ stances

The model shown in Figure 1 can be applied to polymer liquids (polymers in a molten state), at least partially, 51 because the empty places are not big enough to accommodate the whole macromolecules comprised of many 52 thousand linked atoms. In addition, a large amount of activation energy for displacement of whole molecules 53 is needed. According to Eyring, it is 1/4 to 1.3 of the evaporation heat. If one summarizes this value for all 54 repeating units of a macromolecule, one obtains a value which is much larger than the energy needed for breaking 55 the chemical bonds leading to a chemical degradation of macromolecules. By the way, for the same reason the 56 polymers do not exist in a gas statebefore to evaporate the macromolecules decompose usually reaching the 57 monomer state. 58

Solution of this situation can be found if we consider the fact that the independent kinetic units in macromolecules, particularly those comprised of flexible chains, are not the whole molecules but their segments. Then we can assume that the spheres in Figure 1 do not represent single molecules but segments of macromolecules, where between the segments there are also non-occupied places. What is more, for thermodynamic reasons, the number of these free places strongly increases with the rise of temperature. The more they are in a unit volume

64 the more flexible are the molecules.

For flexible macromolecules it is possible the displacement of small sections of molecule without involving the rest of them, and for this are not needed large activation energies. It is experimentally proven when the growing molecule reaches the size of the segment, the activation energy of the viscous flow does not depend any more on the degree of polymerization. Just due to the subsequent displacement of small sections of macromolecule it is possible to move the whole molecule; the direction of this displacement is determined by the external force. It follows that polymer molecules moves not via "jumping" of whole molecule but via displacement of its small sections similarly to the movement mechanism of reptiles and worms.

The above-described model is applicable to polymers with not extremely high molecular weight, at least below their critical chain length, which for vinyl polymers equals twice the weight-average degree of polymerization. This limitation is related with the onset of entanglement and a modified model is required to account for the ability of long chains to translate and diffuse through the polymer matrix.

76 **4** II.

77 The "Reptation Model"

The problem of diffusion mechanism of large flexible chains was solved by de Gennes [2] and Edwards [3], 78 who formulated the fundamental concept of "Reptation model". In the de Gennes approach, the polymer chain 79 is assumed to be confined in a hypothetical tube, the contours of which are defined by the position of the 80 entanglement points in the network. In this way, the single polymer chain, trapped inside the "tube", is not 81 allowed to cross any of the obstacles. This situation is presented graphically in Figure ??a. The macromolecules 82 may move in a snake-like fashion among the obstacles, that is via reptation [2]. Lateral chain motion is severely 83 restricted by the presence of neighboring chains. Mechanistically, reptation can be viewed as the movement of a 84 "kink" in the chain along its length (Figure ??b). The amorphous polymers are the most often studied ones, as, 85 for example, the polybutadiene because of its low glass transition temperature and high chain flexibility at room 86 87 temperature.

Figure ??: Schematic representation: a) -a polymer chain confined in a hypothetical tube contoured by fixed obstacles (depicted by dotted lines), and b) -movement of a "kink" along the chain until it reaches the end of the chain and leaves it. Successive motions of this kind translate the chain trough the tube and eventually take it completely out of the tube

91 it completely out of the tube.

92 **5** III.

93 Further Development of the "Reptation Model" and its Criticism In a quite early time [4] it was well understood 94 that the mobility and self-diffusion of polymer molecules in concentrated systems or in the molten bulk state is 95 largely controlled by entanglements between the molecules. These entanglements are a result of the chain-like 96 nature of the molecules and of their extended, coil-like configuration. The conformation and mobility of polymer molecules in dilute solution, which are relatively simpler case, helped in consideration of self-diffusion in the more 97 concentrated states and in the bulk polymer melt. The molecular self-diffusion controls several special properties 98 of polymers as transport of biological macromolecules within living tissue, the morphology of semi-crystalline 99 polymers and the flow properties of plastic melts -these are part of a broad spectrum of polymer properties 100

101 controlled by the rearrangement and diffusion of polymer molecules.

Although the nature of polymers has been recognized for several decades, it is relatively later that a clear 102 understanding of their self-diffusion in concentrated systems has begun to emerge. The physical picture is rather 103 different to that associated with non-polymeric materials as mentioned in the Introduction. There are essentially 104 two reasons for this: the sheer size of the molecules involved, and their intertangled nature. A typical polymer 105 molecule consists of several thousand monomer molecules, connected as a long flexible chain; in addition, it may 106 adopt an exceptionally large number of different configurations, because there is, generally, easy rotation about 107 the backbone bonds [5]. In the bulk material, this chain folds up in the form of a loose coil, occupying a volume 108 many times that of the chain itself. Since the volume of the coil not occupied by the chain is nonetheless filled with 109 polymer, it follows that any given polymer molecule is interpenetrated by, and intertangled with other molecules 110 very intimately. Because of this, a polymer chain cannot diffuse by random thermal hops in which it moves as 111 a single unit, as is essentially the case with smaller molecules and atoms as described above. Its translational 112 motion, rather, and the way in which it disentangles itself from its neighbors, are cooperative processes, which 113 represent the sum of random motions of all monomers along the chain; a polymeric molecule may thus be subject 114 to long-range interactions -such as entanglements, which small molecules do not experience [4]. 115

Fundamental contributions to the development of the ideas of self-diffusion in polymer melts have done by L. Leibler, M. Rubinstein and R. Colby covering polymers with various architecture, structure, composition, and other characteristics (e.g. [6][7][8][9][10][11][12][13][14][15][16]).

A peculiarity of almost all studies on relaxation and self-diffusion of a polymer chain in a melt is that these studies concern exclusively non-condensation polymers, typically polyolefins. To them belong hydrogenated polybutadiene used for evaluation of the self-diffusion coefficient in its melt [17], polyethylene and polystyrene, used for studying the molecular weight and temperature dependence of self-diffusion coefficients [18]. Stars, combs, rings, and polydisperse samples have been used to get a new information on diffusion mechanisms [19].

The self-diffusion coefficient and zero-shear viscosity have been measured in the melt state for a series of threearm star hydrogenated polybutadienes [20]. Poly (vinyl) acetate-toluene and Neoprene-acetone have been used for evaluation of the diffusion coefficients in polymer-solvent systems for highly concentrated polymer solutions [21].

Self-diffusion and tracer diffusion of hydrogenated and deuterated polybutadienes, both above the entanglement molecular weight have been investigated over a broad range of molecular weight to study the reptation and constraint release in linear polymer melts [22].

In the rather rare publication on polyesters [23] the growth of branched polymer structures up to the gel point has been examined a polyester system at two different branch agent concentrations. In all cases, scaling relationships between various properties were displayed for the whole range of molecular weights [23].

In a review on the tube theory of entangled polymer dynamics [24] it is stated that the dynamics of entangled 134 flexible polymers is an appealing interdisciplinary field where experimental and theoretical physics can work 135 closely with chemistry and chemical engineering. Further on, the role of topological interactions is particularly 136 important, and has given rise to a successful theoretical framework: the "tube model". In the same review are 137 discussed specially synthesized model materials, an increasing palette of experimental techniques, simulation and 138 both linear and nonlinear rheological response. It is concluded [24] that our current understanding of a series of 139 processes in entangled dynamics: "reptation", "contour length fluctuation" and "constraint-release" are set in the 140 context of remaining serious challenges. Especial attention is paid to the phenomena associated with polymers 141 of complex topology or "long chain branching". 142

Even stronger effects of molecular topology on diffusion have been observed for entangled DNA molecules [25].Among polymers, DNA is rather unique in that it is naturally found in several different topological forms, including linear, supercoiled circular, relaxed circular, knotted circular, and branched. When long polymers such as DNA are in a highly concentrated state, they may become entangled leading to restricted self-diffusion. The effect of molecular topology on diffusion in concentrated DNA solutions was investigated and surprisingly large effects were found. It was concluded that the diffusion in entangled DNA solutions strongly depends on topology of both the diffusing molecule and the surrounding molecules [25].

The same problem, namely the entangled polymer dynamics beyond reptation was recently [26] treated in detail. For this purpose, linear and cyclic ds-DNA molecules as model system was used, and a new singlemolecule characterization platform by combining super-resolution fluorescence imaging and recently developed single-molecule tracking method, cumulative-area tracking, which enables to quantify the chain motion in the length and time scale of nanometers to micrometers and milliseconds to minutes.

It is manifold demonstrated that the rheological properties of polymer materials microscopically arise from 155 entanglement of polymer chains [2,3]. Decades of theoretical, experimental [27][28][29][30][31][32], and simulation 156 studies [33][34][35] suggested that topological states of polymer (e.g. linear, cyclic, etc.) have significant effect 157 on entanglement mode between the chains [36]. Recent studies demonstrated that the topological states of 158 polymer chain are one of the key factors that regulate macroscopic physical properties of polymer materials, 159 including thermal stability of polymer micelles [37,38] and elastic properties of polymer gels [39]. Nanoscopic 160 characterization of the entanglement between topological polymers at the single-chain level would thus provide 161 a foundation for the development of new polymer material. 162

Motion of a linear polymer chain under entangled conditions has been described by reptation theory [3]. In this theory, as already mentioned, a polymer chain is confined in a transiently existing virtual tube created by

entangled surrounding chains. Due to this spatial confinement, the chain cannot move transversely across the tube 165 and displays motion only along the tube as can be concluded from Figure ??. According to this model, motion of 166 the entire chain is determined by the motion of two ends of the chain. It is obvious that the reptation theory cannot 167 fully describe the motion of topologically unique cyclic polymer chains under entangled conditions as cyclic chains 168 do not have chain end [26]. Several theoretical frameworks describing motion and relaxation of entangled cyclic 169 chains have been proposed, including double-folded reptation, lattice-animal, constraint release, and once threaded 170 model [40][41][42][43][44]. Contribution of mutual relaxation between entangled chains and decoupling of diffusive 171 motion and chain relaxation on entangled cyclic polymer dynamics have also been suggested [45,46]. Compared 172 with well-accepted reptation model for linear polymers, cyclic polymer dynamics remains elusive [26]. 173

Nuclear magnetic resonance spectroscopy, light and neutron scattering, and viscosity and stressrelaxation 174 measurement have been main tools for characterizing polymer dynamics [47][48][49]. Reptation model has been 175 confirmed for linear chains using natural polymers such as DNA [50] and actin filament [51] as well as synthetic 176 polymers [52]. In these studies, although motion and conformational state of single chain were captured directly, 177 quantitative analyses were often conducted based on overall motion and relaxation of the chains such as chain-178 length-dependent motion of center of mass [26]. Using this new method [26], it was demonstrated that the motion 179 of the linear chains under entangled conditions occurring at the level of both whole chain and entangled segment 180 181 are consistent with the reptation model. The results obtained suggest also that the motion of the cyclic molecule 182 at the whole chain level is distinct from that of the linear chain because of the topological constraint of the cyclic 183 chain under entangled conditions rather than topology-dependent local chain motion and interaction. It was also proved the existence of hypothesized but unproven modes of the motion of cyclic chains under entangled 184 conditions, including amoeba-like motion of double-folded loop-like region [26]. 185

From this brief review of the development of the reptation theory it could be concluded that the Reptation 186 model can be applied for explaining the self-diffusion mechanism of polymers comprised of flexible chain-like 187 macromolecules, which preserve their chemical composition (even at elevated temperatures, e.g. their melts) 188 during the diffusion process, that is, the diffusion is not paralleled by chemical reactions. The noncondensation 189 polymers inherently fulfilled these characteristic requirements. On the contrary, the condensation polymers 190 are distinguished by chemical peculiarities, which make the application of Reptation model for describing the 191 diffusion in their melts questionable. The subsequent sections of this review deal with the chemical peculiarities of 192 condensation polymers, which could help us in answering the question regarding application of Reptation model 193 to the melts of condensation polymers for explaining of their diffusion mechanism. Finding of this answer is just 194 the target of this study. An additional reason for treating the condensation polymers in this respect is the fact 195 that the reptation theory was supported by experimental results from studies of exclusively non-condensation 196 polymers. 197

198 **6** IV.

The Chemical Peculiarities of Condensation Polymers [53] At the beginning let remind a basic knowledge in the polymer science. Polymers are synthesized mostly by two chemical reactions: polycondensation and polymerization. In the first case the functional groups (e.g. -COOH, -OH, -NH 2, and others) of the monomers react and a low molecular weight product (usually H 2 O) is separated. In the second case the reaction goes via opening double or triple bonds, or cycles and no low molecular weight product is separated.

Another basic difference between the two processes is the fact that in the case of polycondensation, at the ends of the formed macromolecules remain functional groups capable to react further if the respective conditions are available.

In the case of polymerization such an opportunity is missing (a rare exception is the "living" polymerization). The two basic chemical reactions for polymers synthesis look like this: Polycondensation:HOOC-R-COOH + HO-R?-OH ? HO(-OC-R-COO-R?-O-)H + H 2 O

210 (1) polyester Polymerization:nCH 2 =CH 2 ? (-CH 2 -CH 2 -) n

(2) polyethylene Some polymers, regardless of their type of synthesis, contain as side groups various functional
groups (-OH, -NH 2, -COOH and others), which can undergo chemical reactions with similar groups of another
polymer if the respective reaction conditions (heat, catalyst, vacuum, etc.) are present. These reactions have the
specificity that they do not involve the backbone of macromolecules but their side groups only [5].

The condensation polymers, in addition to this type of reactions, can realize also chemical interactions with the participation of backbone atoms [54,55]. The most typical are the trans-(exchange-) reactions and the additional polycondensation:

Additional polycondensation: M n + M m ? M n + m (3)

²¹⁹ 7) two molecules one molecule

220 Trans-(exchange-) reactions:(4)

221

These reactions take place during the heat treatment of linear polyesters or polyamides (as well as their blends) at elevated temperatures (close to the melting point -above or below!), particularly in vacuum or in an inert gas flow. The additional solid-state condensation involves the chain-end groups, and the transreactions -the near situated intrachain-or interchain-groups.

The basic difference between the described two types of reactions, (eqs. (3) and (??)) is that in the case of additional reactions two macromolecules yield only one new macromolecule, (eq. (3)), while in the transreactions the starting two macromolecules form two new ones, each of them comprising a part of each of the reacting chains, (eq. (??)).

Eventually, the additional polycondensation is accompanied by an increase of the molecular weight in contrast to the transreactions, in which the average molecular weight is unchanged [5,54,55].

Further on, the transreactions lead to formation of block copolymers (e.g. polyesteramides, as shown in the above example, eq. (??)) if the reacting macromolecules differ in chemical composition.

For a couple of decades, the solid-state postcondensation has been a well-known process [55][56][57][58][59][60] particularly in the case of poly(ethylene terephthalate) (e.g. [61]). The effect of numerous factors (temperature, duration, particle size, medium, etc.) on the molecular weight increase for polyesters and polyamides has been

237 intensively studied and described mainly in the patent literature, because of the technological importance of this 238 process.

Exchange reactions of polyesters are usually carried out in a molten state (ca. 5-10 °C above T m). It has been shown by careful investigation [62] that ester interchange reactions of poly(ethylene terephthalate) (PET) can take place 20-30 °C below T m, e.g., in the solid state. In the solid state, the rate of reaction of this polymer becomes relatively high at temperatures above 225 °C and is catalyzed by the free carboxylic end groups of the polyester [62].

a) The additional (post) polycondensation and the exchange-(trans) reactions in polymer science and 244 technology Among the condensation polymers, possibly, the most important are the polyesters and polyamides 245 (Nylons). This is related with their first and very wide application as textile and technical fibers. Some later, 246 particularly the polyamides, were applied as engineering plastics and during the last 2 -3 decades PET found 247 a large application as packaging material (mostly for bottles of pressurized soft drinks). It turned out that 248 PET is non-replaceable material in this respect due to its transparency, chemical resistivity, gas and vapor 249 nonpermeability, light weight, and others, and for these reasons it enjoys 10% annual increase in its production 250 [63].251

Discussing these three rather different areas of applications of condensation polymers it seems important 252 to mention that for each of these cases one must apply a different processing technique: fibers are produced 253 by spinning, engineering plastics -via injection molding, and PET bottles -by means of injection molding and 254 extrusion. For the spinning process one needs polymers with molecular weight around 20 000 because their melt 255 viscosity corresponds to the required viscosity for performing of spinning process. Luckily, this is the molecular 256 weight of the polycondensates after their primary synthesis. For using the injection molding, and particularly the 257 extrusion, for processing the same polymers much higher melt viscosities are needed. Unfortunately, they cannot 258 be reached during the primary synthesis of polymers because of the drastic increase of melt viscosity making 259 further stirring of the reaction mixture impossible. 260

The solution of the problem has been found in using one of the chemical peculiarities of condensation polymers -their ability to undergo additional (post) condensation even in a solid state, as mentioned above. On the commercial importance of these reactions firstly stressed Flory in the mid-thirties of last century [55] and later described in the open (e.g. [64]) and mostly patent literature because of its commercial relevance.

The additional condensation in solid state is carried out with chips synthesized for fiber production in a reactor (usually under vacuum) at temperatures close but below melting for a couple of hours. Obviously, the importance of the solid-state additional condensation will steadily increase since the increasing needs of packaging materials -because of bad packaging 50% of the food in the developing countries is spoiled, while in UK this amount is 2-3% [65].

The exchange reactions between condensations polymers also play a significant role in polymer science and technology. Let mention the case of polymer-polymer composites only. The mechanical performance of composite materials depends primarily on the adhesion quality on the interface between the matrix and reinforcement for effective transfer of the load between the two-basic component of the composite. In case these components represent condensation polymers, due to the exchange reactions an ideal adhesion is realized because of establishing chemical bonds between the matrix and reinforcement (e.g. [66,67].

Quite similar is the case with the compatibilization phenomenon in polymer blends and polymer-polymer composites involving condensation partner. Since by far the most of polymer pairs are thermodynamically nonmiscible, for improving of their compatibility a third component, a "compatibilizer" is used, similarly to the surfactants in low molecular weight mixtures. A good example in this respect is the malleated polypropylene (PP) used in blends and composites of PP with polyesters and polyamides. Maleic anhydride undergoes to trans-reaction with the condensation partner (e.g. [68,69]).

²⁸² 8 b) Chemical healing in condensation polymers

283 Self-healing is a well-known phenomenon in nature. The concept of "self-healing" of synthetic ma-284 terials emerged a couple of decades ago and continues to attract scientific community progressively 285 [70][71][72][73][74][75][76][77][78][79]. Self-healing polymers and fiber-reinforced polymer composites possess the ability to heal in response to damage wherever and whenever it occurs in the material. To date, self-healing has
been demonstrated by three conceptual approaches: capsule-based healing systems, vascular healing systems,
and intrinsic healing polymers [70,71].

When two samples of the same amorphous polymer are brought into good contact at a temperature above the glass transition, the interface gradually disappears, and the mechanical strength of the polymer-polymer interface increases until, at long contact times, the full fracture strength of the bulk polymer is regained. At this point the junction surface has become in all respects indistinguishable from any other surface that might be located within the bulk material -the junction has "healed." Year 2021

In a recent [80] detailed review on the chemical and physical aspects of self-healing materials it is stated that "Due to limited chain mobility and a lack of bond reformation abilities, common polymers do not show selfrepair attributes" [80]. How does look the situation in reality?

The earliest systematic studies of healing in polymers were related with autoadhesion (direct bonding or self-297 bonding) and adhesion of polymers [81] undertaken by Voyutskii [82], who proposed a molecular interpretation 298 based on the diffusion of macromolecules. Some later, around 80-ies of the last century, the crack healing in 299 polymeric materials has been a subject of intensive investigation summarized in recent reviews [81,[83][84][85]. 300 To the same period belongs the formulation of the fundamental concept of "Reptation model", done mostly by 301 302 de Gennes [2] and Edwards [3]. Their idea was immediately implemented in the molecular interpretation of the healing process [80,81,83]. The amorphous polymers are the most often studied ones. The crack healing 303 304 is modeled at microscopic level by the following healing parameters: (i) center-of-mass Fickian interdiffusion in the healing of elastomers, (ii) average chain segment displacement and formation of new entanglements in the 305 interfacial regions, (iii) change in crossing density of molecular chain end [80,83]. 306

The self-diffusion in a bulk polymer helps to understand the healing process in the best way, but the two processes are not identical [83]. In the case of selfdiffusion, the coils move over distances many times their mean diameter, whereas healing is essentially complete in the time it takes a polymer molecule initially next to the junction surface to move halfway across it. The healing time may take minutes, hours, or even days depending on the healing temperature and polymer characteristics [83]. Configurational relaxation in the bulk polymer is usually described by the "Reptation model" [2,3].

The described cases of self-repairing could be called physical healing so far one deals with samples which have not been subjected to any chemical treatment prior or during the healing process. An additional reason to precise the terminology is the fact that around the same time (1984) it was demonstrated that self-repairing is possible also because of chemical reactions in the same one-or two-component chemically non-treated polymers [86].

This was possible because a special attention was paid to linear condensation polymers. Like other classes 317 of polymers, their chain flexibility increases with increasing temperature. Besides this physical process during 318 the heating, as mentioned foreheads, chemical changes are also possible. In addition, the diffusion of low-319 molecular-weight fractions to the surface is a wellknown phenomenon for poly(ethylene terephthalate). Such an 320 enrichment of the surface on reactive chain-end groups will enhance the chemical reactions on the surface. It 321 seems quite reasonable to expect that these reactions could take place at the interface between two samples of 322 polycondensation polymer if (i) the contact is good enough, and (ii) suitable reaction conditions are created [86]. 323 This assumption is supported by the observation mentioned above [62] that ester interchange reactions of 324 poly(ethylene terephthalate) take place 20-30°C below T m, that is, in the solid state. 325

The new molecular mechanism for the healing phenomenon in semicrystalline linear polycondensates, that is 326 healing resulting from chemical reactions between macromolecules located in the interfacial surface, has been 327 demonstrated by means of strips of commercial PET film. They have been annealed at 258 o C to increase 328 their T m up to 260 -268 o C thus avoiding melt sticking during the subsequent heat treatment [86]. Two 329 such strips are partially overlapped as shown in Figure 3, pressed, and heated in a vacuum at 240 o C for 10 330 to 100 h. By measuring the stress at break, ? b , outside the contact area and the debonding shear stress, 331 ? i, the critical overlapping length, l, has been computed. Further experiments [87] lead to the conclusion 332 that transreactions contribute more than solid-state post condensation to the chemical healing. If two linear 333 condensation specimens are undergoing the stage of wetting [80,83], and the temperature is high enough, the 334 solid-state post condensation and interchange reactions start. They result in the completion of the last two stages 335 (diffusion and randomization) [80,83]. An interesting assumption could be formulated in this case, namely, that 336 to achieve a given extent of recovery, the "chemical" healing needs less time than the "physical" one. There are at 337 least two reasons for this: (i) the "chemical" healing is less diffusion controlled (the most important factor seems 338 to be the perfection of the contact) and (ii) the chemical interaction is possible even in the amorphous areas of 339 the crystalline regions, as schematically represented in Figure 4. The diffusion (e.g., mutual interpenetration of 340 the chains) is considered only in amorphous regions (Figure 4.), which for PET represent less than 50% of the 341 surface [86]. Summarizing t could be concluded that the experiments described demonstrate a new molecular 342 mechanism of the healing phenomenon in semicrystalline linear polycondensates -healing because of chemical 343 reactions between neighboring macromolecules located in the interface surface. To distinguish this case of self-344 repairing from the previous case, the physical healing, it has been suggested [86] to be called chemical healing. 345 Evidently, the chemical healing is quite a general property for all condensation polymers characterized by the 346

ability to undergo transreactions and/or additional condensation. R. Porter [68] has acknowledged this fact in his

review on compatibility and transesterification in binary polymer blends as well as done in the recent monography of H. Kricheldorf [54] on polycondensation.

The common characteristic feature between the physical healing and the chemical healing is the fact that they are observed with chemically non-treated or modified polymers. The self-repairing in these two cases is related with the two basic and inherent properties of macromolecules -the ability to diffuse as well as to undergo chemical reactions (for condensation polymers only!). It seems quite reasonable to call just these two cases of self-repairing "self-healing", since the respective polymers have not been subjected to any chemical treatment before performing the healing procedure or during their primary synthesis by adding a specific comonomer.

At the same time, in the last decade it has been noted that a few classes of reactions (currently they are at least 15 types [88]) offer self-repairing through the cleavage and reformation of specific bonds [80] but these cases hardly could be called "self-healing". The reason for this statement is that to perform this type of healing the respective polymer must be subjected to specific chemical treatment or during its basic synthesis a special comonomer must be used. Possibly, for such cases of self-repairing it would be more accurate to use the term "chemically assisted healing".

The importance of the lack of external chemical intervention in proceeding of the self-healing processes is supported also by the interpretation of the term itself. According to Cambridge dictionary, "self-healing" means "to describe a piece of equipment or system that has the ability to discover and correct faults without needing outside help".

Discussing the terminology aspect of the selfrepairing phenomenon, one must add that the abovedescribed case of chemical healing with condensation polymers could be further specify as homochemical healing [86,87] since it has been demonstrated [89] that chemical healing can be observed also if two chemically different condensation polymers are subjected to healing procedure. In such a case one deals with heterochemical healing. Such type of healing has been observed on two pairs of samples -PET and Nylon 66 as well as poly (butylene terephthalate) (PBT) and Nylon 6 [89].

All the above-described experiments on chemical healing [86,87,89] mobility due to the great rigidity of their 372 macromolecules, as for example the case with cellulose is [90]. Multi-layered sheets of cleanex (fibrous delignified 373 native cellulose) have been annealed at temperatures between 120 and 265 o C under or without pressure. The 374 tensile testing demonstrated that the strength is four times and modulus -eighteen times higher for the pressed 375 sample than the non-pressed ones. A conclusion is drawn [90] that the observed welding cannot be attributed 376 377 to diffusion of macromolecules through the interface; it is due mainly to solid state chemical reactions at the contacting surfaces. It should be mentioned that this same conclusion led to the healing experiments with a 378 liquid crystalline polymer [91]. 379

Further on, an attempt has been made to evaluate in a more precise way the contribution of solidstate chemical reactions to the healing effect between two contacting bulk pieces via chain mobility restrictions on a series of polyamides (Nylon 11, Nylon 12, and Nylon 66) [92]. Strips with higher melting temperatures have been obtained by annealing. To suppress the chain mobility in amorphous regions and to exclude or greatly minimize the diffusion of macromolecules during the healing process, the samples have been partially (only in amorphous regions) cross-linked using the technique of Arakawa et al., [93] based on methoxy methylation.

After such pretreatment of the samples the healing procedure is performed with partially overlapped strips (Figure 3) at temperatures enough below their respective melting to avoid sticking. Since at these healing temperatures the chains in crystallites are also immobilized, one can conclude that the observed welding effect is due exclusively to the chemical reactions on the contact surfaces.

The best proof for the dominant role of the solid-state chemical reactions in the healing process in linear condensation polymers is the observation that under the same healing conditions, the cross-linked samples of Nylon 11 display much higher shear stresses than un-cross-linked ones. It should be added that with crosslinking the shear modulus also changes, which affects the shear stress. If the diffusion of macromolecular chains is the controlling factor in the healing, then dealing with cross-linked samples one must observe the reverse situation [92].

A common characteristic feature of transreactions and the additional condensation regarding the healing effect 396 is that they are possible only if the reaction partners are close enough in the space. Further on, if one considers 397 that the concentration of the partners for transreactions is much higher than that of the terminal groups and 398 that crystallinity and crosslinking suppress mobility, it follows that the probability of collision of the terminal 399 groups is drastically reduced. At the same time crystallization and cross-linking lead to an increase in the rate 400 of transreactions, due to an increase in the concentration of stressed contact points [95]. In such a situation, 401 the transreaction processes are favored, and it can be concluded that the healing effect is mainly a result of 402 transreactions [92]. 403

A jump in the temperature dependence of the shear stress of Kepton-H and Upilex-R is worth mentioning. The increase of the activation energy could be explained by chemical reactions taking place at the contacting surfaces [96].

The fact that the healing process is carried out at temperatures below the glass transition temperature of the respective polymer where the molecular diffusion is excluded, gives an idea about the contribution of the physical processes to the healing, that is, the welding in this case is due exclusively to the chemical processes [96].

410 9 c) Sequential reordering in condensation copolymers via tran 411 sreactions

The study of transreactions started with the pioneering work of Flory [55]. These reactions have been convincingly 412 confirmed, as mentioned in the previous sections, by studying blends of protonated PET with deuterium labelled 413 414 (d4) PET by SANS; they take place rapidly in the melt as well as at lower temperatures (some 20-30 o C below the melting of PET [62]) resulting in formation of a block copolymer [97]. In the subsequent years they have 415 been widely used for preparation of condensation copolymers starting from blends of homopolymers (e.g. [98]). 416 The blends are converted first into block copolymers and finally into random copolymers because all repeating 417 units are equally likely to react. Therefore, the properties of a blend in which transreactions are possible depend 418 on the rate and degree of completeness of exchange reactions. 419

420 In fact, any type of sequential order is characterized by the properties, mostly physical ones.

As a matter of fact, the most serious support in favor of conclusion about dominating role of chemical reactions in self-repairing process are the healing experiments with polyimide films characterized by extremely high values of their glass transition temperatures, T g [96]. For example, T g of Upilex-R (polyimide) is 285 o C, and that of Kepton-H (polypiromellitimide) -between 360 and 410 o C. The healing experiments have been performed in the way described above for other polymers, as well as their testing. The applied healing temperature (T h) has been 250 o C, that means below or far below their T g -values.

The selected healing temperature has two important peculiarities: (i) it is high enough for performing of chemical reactions, and (ii) it is not high enough for realization of molecular movement since the respective polymer is at temperature below its T g where such movement is excluded.

For example, a copolymer with blocky sequential ordering should crystallize if at least one of the starting 430 homopolymers is crystallizable and that a copolymer with random type of sequential ordering is noncrystallizable. 431 The study of the behavior of the crystalline phase(s) can offer an insight in the occurrence and depth of chemical 432 433 interactions between the blend components as well as in the sequential order in copolymers. At the same time, the 434 properties of the amorphous phases will support these conclusions since at the stage of complete randomization, particularly in equimolar blends of condensation polymers, a single glass transition should be observed instead 435 436 of the two glass transitions, typical of a mechanical blend or of a block copolymer as shown in Figure 5. The method of dynamic-mechanical thermal analysis (DMTA) is commonly considered as the most reliable technique 437 for the determination of T g and for this reason it was applied to the PET/PA 6 blend subjected to drawing and 438 annealing. The results are summarised in Figure 5 [99]. 439

Evidence derived from the behavior of the crystalline phases has been obtained on the same blend of PET 440 with polyamide 6, subjected also to drawing after extrusion and annealing for various times around the melting 441 442 temperatures of the blend components [100]. Wide-angle X-ray scattering (WAXS), Figure 6, demonstrates that 443 the thermal treatment at 220°C for 5 h (Figure 6a) results in a crystalline highly oriented polymer blend. The 444 situation changes drastically after annealing at 240°C for 5 h (Figure 6b)the PA 6 diffraction patterns are in the form of Debye rings, suggesting isotropy of that component. At the same time, the orientation and perfection 445 446 of the crystallites in the PET fraction remain unchanged. Prolonged annealing (25 h) at the same temperature (above T m of PA 6!) leads to the almost complete disappearance of the PA 6 Debye rings (Figure 6c). 6b). 447 Figure 6c proves that PET preserves its orientation during annealing at 240 o C, that is, it remains in a solid 448 state. On the possibility of performing of chemical reactions in a solid PET (some 20 o C below melting) was 449 indicated even earlier [62]. 450

What is more, the same data from WAXS (Figure 6c) and from DSC (Figure 7, curve (f)) demonstrate that the total amount of PA 6 react with the half of the PET only since the other half builds the crystallites, which are not involved in the chemical interactions (typically, the maximum crystallinity of PET is 50%).

To the same conclusions leads the testing of the same samples by means of differential scanning calorimeter (DSC) [100] as demonstrated by the respective curves displayed in Figure 7. These observations indicate that after such a thermal treatment, the total amorphous PA 6 is involved in a copolymer with the amorphous PET. The behavior of both, the crystalline (Figures 6 and 7) and amorphous [99] phases clearly indicates that the PA 6 starting component does not exist anymore as individual component. This is due to its involvement in a copolymer with a supposedly random structure because of transreactions taking place during prolonged annealing at elevated temperatures.

It should be mentioned that the described chemical changes are proven also by following the behavior of other physical properties during melt annealing at various temperatures and durations. For example, application of IR spectroscopy after selective extraction with formic acid, accompanied by weight control of the fraction supports the above conclusions. The weight loses after extraction are given in Table ??. The involvement of the total starting amount of PA 6 into a copolymer with PET has been demonstrated also by selective (only PA 6) dying with wool-type dyestuff -a complete homogeneous dying of the thin slices on the microphotographs after the final treatment is observed, contrasting the partial dying in the nontreated samples [101].

The exchange reactions and particularly the sequential order in condensation copolymers prepared via interchange reaction in blends of condensation homopolymers have been studied by Lenz et al. (e.g. [103], Devaux et al. (e.g. [104]), Economy et al. [105,106] and others. The first systematic study on the factors determining the sequential order in these copolymers has been performed by Fakirov et al. (e.g. [107]). These 472 studies ([107]) have been based on the understanding that the exchange reactions resulting in randomization of 473 the copolymers are the same as those leading to regeneration of the blocky character of the copolymers, that is, 474 the sequential order is not determined by the exchange reactions but by other factors present in the system at 475 the given conditions.

The exchange reactions are a tool only for realization of one or other sequential order, they do not determine this order! About the type of the sequential order in these studies (e.g. [103]) it has been judged exclusively from the crystallization (T m) and glass transition (T g) behaviors.

479 What is more, using these factors it is possible to control the sequential order in condensation copolymers as 480 it will be demonstrated below.

481 10 i. Melting-induced sequential reordering in condensation 482 copolymers

The clearest case regarding the factors determining the type of the sequential order is that of the meltinginduced sequential reordering. It is generally accepted that because of direct interchange reactions, the blend of homopolymers transforms into a block copolymer which subsequently turns into a random one:(A) n + (B) m? ...(A) x -(B) y -(A) z ????ABBABAABA???(5)

In the case of ester-ester interchain reactions at elevated temperatures, usually above T m, the randomization is driven only by the large entropy increase originating from the transition of the block copolymer into a random one. This results in the final randomization of the blend and in a drastic change of its properties -crystallization ability, solubility, transition temperatures, etc.

Performing experiments with blends of crystallizable or non-crystallizable polycondensates, the Year 2021 491 However, the losses depend strongly on the annealing temperature -for the thermally untreated samples they 492 are about 100% whereas after annealing at 240°C for 25h they drop to about 20% (Table ??, samples (a) and 493 (f)). It can be concluded that practically the entire PA 6 fraction is extracted in thermally untreated samples, 494 495 in contrast to those annealed at 240°C for 25 h. The rise in the intensity of the IR absorption band at 3300 cm -1 , as well as in the range of 2200-2800 cm -1 , which is characteristic of the vibrations of the -CH 2 -groups, 496 follows the same trend since the copolymer is enriched in -CH 2 -groups, as compared to homo-PET [102]. Thus, 497 it is quite clear that the amount of PA 6 incorporated in a copolymer increases with the rise of the annealing 498 temperature and duration. 499

It has been demonstrated [104] that the rates of the direct and reverse reactions are identical. This is quite 500 understandable, considering that the bonding energies of broken and reformed bonds are almost the same in both 501 directions. Nevertheless, randomization proceeds as a practically irreversible process (under given conditions) and 502 eventually a random copolymer obeying Bernoulli statistic is formed [104]. partners being thermodynamically 503 miscible or nonmiscible, it has been unambiguously demonstrated that annealing above the melting temperature 504 505 results in a complete randomization. At the same time annealing the random copolymer below the melting temperature (some 20 o C) leads to the restoration of the blocky structure. Figure 8 demonstrates these two 506 cases for the blend PET/polyarylate (PAr): 507

Considering the fundamental statement that transreactions do not determine the type of sequential order and 508 that they are just a tool for its realization, it might be possible to observe such a situation, when other factors 509 appear in the system, acting more strongly than and in opposition to those causing randomization to take place. 510 A good example in this respect is the crystallization. It becomes effective when a randomized condensation 511 copolymer is brought to a temperature below the melting of the crystallizable blend component. Figure 9 512 illustrates schematically the transition from a random into a block copolymer, suggesting that crystallization is 513 the driving force for sequential reordering after cooling a randomized copolymer to a temperature below the T 514 m of the crystallizable component. It is quite evident that sequences of 2-3 repeating units are not long enough 515 to form a lamella of thickness l c. The lowest values of l c are about 50-60?, as demonstrated for poly(butylene 516 terephthalate) copolymers [109]. Assuming these values of l c to be the lower limit and considering that the length 517 of the PET repeat unit in the chain-axis direction is about 11?, it is easy to conclude that crystallization of PET 518 can occur only if PET blocks of at least 5-6 repeating units are available. This axiomatic requirement can be 519 considered as the basic driving force toward the blocky structure when crystallization conditions are established 520 [107]. another important peculiarity of crystallization-induced sequential reordering. Formation of lamellae of 521 thickness l c not only stimulates sequential reordering in favor of the blocky structure, but also restricts the block 522 length to the value of l c so one can speak in this case of "microblock copolymers" with quite uniform block 523 length distribution, that is controlled block regeneration. 524

⁵²⁵ 11 ii. Crystallization-induced sequential reordering in conden ⁵²⁶ sation copolymers

Crystallization-induced sequential reordering is only one of the possible cases in which the sequential order in condensation copolymers is changed. It was worth looking for copolymer systems where the transition from a random copolymer to a blocky one is governed by factors not related to crystallization.

⁵³⁰ 12 iii. Miscibility-induced sequential reordering in condensa-⁵³¹ tion copolymers

One can design an equimolar terpolymer in a two-stage preparation process. Let us have three condensation homopolymers (A) n , (B) m and (C) p ; the first two, (A) n and (B) m , are immiscible, while (B) m and (C) p are miscible. During the first stage of preparation, randomization in the A/B blend takes place:(A) n + (B) m? ?ABBBAABBABBABBA?

(AB) n=m (6) After completion of the randomization, the copolymer (AB) n is melt-blended with the third homopolymer (C) p and further randomization occurs, resulting in a random terpolymer:(AB) n + (C) p ? AABCCABBACBCC?. (ABC) n=m=p(7)

The randomization takes place in the melt via interchain reactions at temperatures above the melting points of all crystallizable components as manifold demonstrated (e.g. [98]). If the randomized terpolymer (eq.(7)) is kept for a longer time in the molten state, one can expect changes in the sequential order in favor of the blocky structure:(ABC) n ? ?AAAAABBBBBBCCCCCCC?. ?(A) x - (B) y - (C) z ?(8)

This expectation is based on the miscibility of the homopolymers (B) m and (C) p. Since miscibility requires interaction between longer polymer chains, a tendency toward the formation of longer B-and Csequences should exist. If one considers that transreactions frequently occur in the melt, the formation of blocks (eq. (8)) seems to be very probable as confirmed experimentally [111]. For this purpose, two systems each one comprising 3 homopolymers have obtained confirmed the sequential reordering described schematically by eqs. (??), (7) and (8) [111].

In the above-described cases of sequential reordering in condensation copolymers were discussed the experimental results exclusively from the DSC studies. It should be mentioned that these results and conclusions were supported by parallel studies by means of size exclusion chromatography combined with NMR after selective degradation [112,113]. For some cases it has been used also wide-angle X-ray scattering [110].

In summary, the repeatedly reported randomization of molten condensation block copolymers is observed again and proved by various The model depicted in Figure 9 demonstrates been used. The first one consists of poly(butylene terephthalate)/polycarbonate/polyarylate (PBT/PC/PAr) where PBT and PAr are thermodynamically miscible. The second one involves PBT, PA 66 and PAr, where again PBT and PAr are miscible. In both cases the results techniques sensitive to the changes in the crystalline and/or the amorphous phases. The process is accompanied by a loss of crystallization ability. This melting-induced sequential reordering is driven mostly by the entropy increase.

Restoration of crystallization ability is observed after annealing of random condensation copolymers and attributed to regeneration of crystallizable blocks. This crystallization-induced sequential reordering is driven by upsetting the random ? blockpolymer equilibrium during the annealing of the random system.

Restoration of crystallization ability is also observed in random terpolymers obtained by meltinginduced sequential reordering of ternary homopolymer blends, in which two of the constituents are thermodynamically miscible over the entire concentration range. The effect is established by subjecting these terpolymers to prolonged annealing at the same temperature as copolymer preparation. In this miscibility-induced sequential reordering the process of block restoration is driven by the miscibility factor.

Both randomization and block regeneration are dependent on temperature, transesterification catalyst, and 568 miscibility of blend components. These processes are composition-sensitive and seem to be related to the specific 569 chemistry of the interchange reactions and starting homopolymer structures. The results obtained show that in 570 the transition from block to random copolymer, (i.e., from longer to shorter blocks), the sample crystallizability 571 decreases, attaining eventually a complete amorphization (as revealed by DSC). Likewise, regeneration of melting 572 endotherms in the crystallization-induced reordering process should reflect the restoration of longer blocks of a 573 crystallizable component. All these changes in the sequential order of condensation copolymers affect drastically 574 their structure and properties [114]. 575

The above definitions describing the three most important cases of sequential reordering in condensation copolymers, including also the factors determining the respective type of order, were formulated in refs. [108,110,111], respectively. They were not only well accepted and widely used but were also proven correct through computer modeling and further experiments (e.g. [115]).

It seems important to stress again that all the analysis related with the sequential reordering in condensation copolymers are based on the understanding that exchange reactions do not determine the type of the sequential order; they represent a tool only for realization of a given type of ordering and this type is determined by other factors in the system.

⁵⁸⁴ 13 d) Chemically released diffusion via transreactions

Studying the new phenomenon of chemical healing in condensation polymers [86,87] as result of chemical interactions at elevated temperatures, the concept of "chemically released diffusion" was formulated [89] and supported later by Economy et al. [106]. This aspect demonstrates that mass transfer in condensation polymers at temperatures close to the melting point, as well as in the melt, is paralleled by chemical reactions mostly of exchange type shown above. The contribution of the latter to the mass transfer depends strongly on the temperature, reaction conditions (pressure, catalyst, media, etc.), and most likely on the number of favorable 591 contacts between the different chains. It is to be expected that this number will increase with increasing 592 temperature because of chain relaxation.

The results described above allow to make some inferences concerning the diffusion mechanism for long chains in linear condensation polymers at elevated temperatures. It seems quite likely that the transport of sections of macromolecules through the bulk is due not only to physical diffusion processes but also to chemical ones. If the temperature is high enough, a section of macromolecule (a segment or repeating unit as the smallest possible section) does not remain in its original macromolecule. Due to transreactions between different molecules, some sections frequently change their neighbors. Furthermore, the chemical composition of the section itself could be changed if transreactions occur between chemically different molecules.

In such cases, that is, when transreactions are possible (transesterification, transamidation, transetherification, 600 etc.), we can speak of "chemically released diffusion" of the macromolecular chains as suggested in [89]. This 601 aspect further demonstrates that mass transfer in this type of polymers at temperatures close to the melting 602 point, as well as in the melt, is accompanied by such chemical reactions. The contribution of the latter to the 603 mass transfer depends strongly on the temperature and reaction conditions (pressure, catalyst, media, etc.). It 604 seems that "chemically released diffusion" will not be sensitive to molecular weight. The determining factor is 605 most likely the number of favorable contacts between the different chains. It is to be expected that this number 606 will increase with increasing temperature because of chain relaxation. As demonstrated by measurements using 607 small-angle neutron scattering, these contacts are quite intensive [97]. 608

The presence of entanglements (stressed points) will favor the exchange reactions, as mentioned above [95]. The higher their concentration, the larger the contribution of chemically released diffusion. The efficiency of the stressed points depends on temperature in the same way as in the case of "neighboring" contact and for the same reason.

The concept of chemically released diffusion was seriously supported by similar experiments with chemically cross-linked polyesters performed by Economy et al. [105,106].

Concluding this subsection, it seems interesting to cite an opinion regarding the chemically released diffusion, expressed in a review article on the recent advances of hierarchical and sequential growth of macromolecular organic structures on surface [116]:

"Before continuing, a distinction should be made between "self-assembly", which is commonly used to evoke 618 the formation of both supramolecular and covalent phases on-surface, and "chemically released diffusion". Indeed, 619 numerous published or being published articles comprise the terminology "selfassembly" whereas the right term 620 is "chemically released diffusion". Indeed, "self-assembly" refers to the selforganization of molecular tectons on 621 surface without necessarily involving a chemical modification of the molecular tectons and this terminology is 622 well-adapted for supramolecular phases for which the cohesion is ensured by weak intermolecular interactions 623 624 between elemental building blocks. Contrastingly, chemically released diffusion refers to mass transfer occurring in polycondensates due to the permanent exchange of fragments existing between molecular segments under 625 growth (i.e., via transreactions). This concept developed in the early 1980s by Prof. Stoyko Fakirov is more 626 adapted to describe the formation of covalent phases on surface, the chemical composition of the polymer under 627 growth continuously evolving by exchange reactions" [116]. 628

⁶²⁹ 14 V. Kinetics of Exchange Reactions in Melts of Condensation ⁶³⁰ Polymers

The above rather detailed analyses of the occurrence of additional condensation and exchange-(trans) reactions in condensation polymers was done with the only purpose to demonstrate that these reactions not only exist but they play important role in polymer science and technology. Only using these types of reactions, it is possible to manufacture special polymer materials as bottle grade PET, condensation copolymers from polymer blends, realization of the compatibilization phenomenon in polymer blends, etc.

The same reactions, particularly the exchange reactions, offer a new insight on fundamental theoretical properties of polymer systems as for example the diffusion mechanism in melts and solutions of condensation polymers as demonstrated in the foregoing paragraph dealing with the chemically released diffusion. The evaluation of the contribution of exchange reaction in the diffusion process and its mechanism assumes a better knowledge of kinetics of exchange reactions in melts of condensation polymers.

The fundamental development of the kinetics of condensation reactions in polymer chemistry has been done by Carothers [117] and Flory [55] with later contributions of other researchers [98]. Various techniques have been used for studying the additional condensation and exchange reactions as IR spectroscopy (e.g. [104]), NMR spectroscopy (e.g. [118]), WAXS (e.g. [119]), and others. Of particular importance for the purpose of the current review are the studies performed by means of small angle neutron scattering (SANS) on blends of protonated and deuterated species (e.g. [120][121][122]).

For example, Kugler et al. studied the rate of the interchain transreactions between deuterated and nondeuterated PET chains at 280 o C and calculated approximately 10 transesterification reactions occurring per molecule per minute [97]. This means that for fiber grade PET (with a molecular weight of ~20 000, i.e. degree of polymerization n ~100) each minute fragments of 10 repeating unit leave a given molecule and join another neighboring one. With increase of the melting temperature the exchange reactions become more intensive and the migrating blocks considerably shorter.

The potential for very rapid transreactions in the copolyesters has been demonstrated by heating a 50/50 mixture of the two homopolymers of poly(acetoxy benzoic acid) and poly(2,6-hydroxynaphtoic acid) at 450 o C the rates are more than 100 ester interchange reactions per chain per second [105]! In addition to the temperature, transreactions are favored by the presence of entanglements, as mentioned above -the higher their concentration the more intensive exchange reactions.

The experiments on chemical healing with cross-linked polyamides [92] and polymers distinguished by 658 extremely high glass transition temperatures [96] demonstrated that the chemically released diffusion is a principal 659 mode for mass transfer in condensation polymers. Further on, the mechanism by which the adhesive bond forms 660 in both liquid crystalline polymers and thermosetting polyesters has been investigated using secondary ion mass 661 spectroscopy (SIMS) and neutron reflection techniques [106]. These complementary analytical techniques have 662 been used to examine the entire range of physical and chemical diffusion distances possible in the aromatic 663 copolyesters. Long range effects could be examined by SIMS while neutron reflection would be able to detect 664 localized interfacial diffusion. The contrast across the interface for the aromatic copolyesters has been achieved by 665 observing the interpenetration between thin films of deuterated and non-deuterated copolyesters. No observable 666 changes in SIMS depth profile were registered with annealing after 10 h at 280 o C. Since the depth resolution 667 of SIMS is 500 ?, any changes on the polymer-polymer interface are predicted to occur over length scales of less 668 669 than 500 ?. Neutron reflection data suggest that the actual amount of interpenetration is less than 300 ? after 670 11 h at 280 o C [106]. Completely different is the situation at much higher temperatures. As already mentioned 671 above, in the melt of condensation polymers in each macromolecule, each second takes place breaking the contacts between the neighbouring repeating units. Before establishing a contact (chemical bond) with new (or previous 672 repeating units) the fragment can move, diffuse. However, these fragments move as a single repeating unit (or 673 as small blocks of them) and not as whole long macromolecules. What is more, the macromolecules as long real 674 chains do not exist anymore since the chemical bonds between the repeating units are frequently broken and 675 re-established again (but not necessarily between the previous neighboring repeating units). The macromolecules 676 as stable chains with constant chemical composition appear when the temperature is lowered and the intensity 677 of transreactions is drastically reduced. 678

679 Since the individual films were cured into infinite molecular weight networks prior to joining and annealing, 680 physical diffusion of individual polymer chains or fragments across the interface would not be possible. Thus, 681 the only mechanism available for adhesion across the polymer-polymer interface would be chemical interdiffusion 682 through rapid hightemperature interchain transreactions [106].

663 VI. On the Applicability of "Reptation Model" to Melts of Condensation Polymers

684 Coming back to the basic question regarding the diffusion mechanism in melts of non-condensation and condensation polymers at high temperatures, it seems important to try to assess the applicability of the 685 "Reptation model" to melts of condensation polymers. The presented above data on the peculiar only for 686 condensation polymers chemical reactions and their importance for polymer science and technology demonstrate 687 that the classical picture of self-diffusion in polymers, or the "Reptation model", as proposed by de Gennes [2] 688 and Edwards [3], needs to be complemented. Contrasting the non-condensation polymers where the "Reptation 689 model" is the only mechanism for explaining the diffusion process, the case of condensation polymers seems 690 to be more complex. At lower temperatures (for example, up to T m + 100°C) it looks that the diffusion 691 mechanism is according to the Reptation concept but with some peculiarities -parallel occurring exchange 692 reactions (transesterification, transamidation, transetherification, etc.). If the temperature is high enough, a 693 given fragment no longer appertains to its initial macromolecule. Due to transreactions between different 694 macromolecules, macromolecule's fragments frequently change their immediate neighbors. Furthermore, the 695 chemical composition of such a fragment can change, if transreactions occur between chemically different 696 macromolecules. 697

This process of continuous leaving from a given macromolecule of fragments, which join another macromolecule (or even the same) is schematically presented in Figure 10.

⁷⁰⁰ 15 Two homopolymers

701 16 ?

702 Block copolymer ? Random copolymer (9)

Figure 11: Schematically the diffusion mechanism in melts of condensation polymers at extremely high temperatures (T m + 100 °C and above). The single independent kinetic elements (black particles) are short fragments of macromolecules, comprising one or a very small number of repeating units, which move in any possible direction. Large, flexible, entangled, and stable formations (macromolecules), to which one could apply the "Reptation model" for explaining the diffusion mechanism, are missing. (The motion can be seen by clicking here). The yellow object represents a particle with much larger sizes.

Slightly different is the situation when one deals with a melt of a single polycondensate. In such cases, the first stage is missing, since practically there is no entropic contribution to the mass transfer and the diffusion is related to the Brownian motion only, as visualized in Figure 11.

Let stress again that the main task of this study is to demonstrate that the diffusion mechanism in melts of 712 condensation polymers above some temperatures could be different from the mechanism offered by the Reptation 713 model, which is based on the concept of segmental motion of macromolecules. Above a given molecular weight 714 (or degree of polymerization) independent kinetic entities are not the macromolecules as a whole formation but 715 their segments. The segments comprise one or a few repeating units (in a case of flexible molecules) or the whole 716 717 macromolecule (in a case of rigid molecules as those of liquid crystalline polymers) and allow us to describe the behavior of In molten blends of condensation homopolymers, one can distinguish two stages of diffusion, due 718 mostly to the different driving force of the mass transfer. During the very first moments of chemical interactions 719 between two homopolycondensates, a block copolycondenste is formed, which further randomize in a random 720 copolycondensate according to eq. (??). The driving force for these changes in the sequential order is the 721 entropy increase during the transitions: 722

It is also possible to say that the driving force is the concentration gradient leading to a homogeneous distribution of the two chemically different repeating units in the whole volume.

During the second stage, when complete randomization is achieved, the driving force for the mass transfer is the Brownian motion only. The independent kinetic elements, in this case, are the smallest fragments of macromolecules comprising one or a few repeating units. Their motion is schematically illustrated in Figure 11, where the single black particles represent the fragments, which leave a given macromolecule and join another one. This takes place continuously, resulting in mass transfer in an arbitrary direction. This diffusion mechanism is rather a like to that of the low molecular substances and is quite different from the diffusion mechanism illustrated by the "Reptation model", as recently suggested [123].

polymers by means of the lows derived for the low molecular weight substances [5].

This means that for the describing the kinetic properties of macromolecules (deformations, diffusion, mass transfer, etc.) we are using not the whole molecules but their segments, i.e. much shorter formations than the whole molecules. This approach, namely considering the macromolecules as comprised of many kinetically independent elements for describing many polymer properties is applicable to all polymers, the non-condensation and condensation ones. The same approach is a basic element of the "Reptation model" -movement in a snake-like way.

At the same time, as already discussed, an inherent property of condensation polymers is their ability 739 to undergo intensive interchange (trans) reactions in their melts above some temperatures. This means 740 further dissipation of macromolecules to shorter sections. The situation is like the case of "decomposition" 741 of macromolecules to segments, but there is a substantial difference between the two cases. While segments do 742 not exist as real independent formations, the sections comprising one or a few of repeating units really exist. 743 They not only exist but they move in a rather freeway in the melt as independent kinetic elements. Since their 744 745 sizes are in range of the sizes of the common non-polymeric molecules, their diffusion mechanism must be close to that of low molecular weight substances and different from the diffusion mechanism of macromolecules suggested 746 by the Reptation concept. 747

The fact that the macromolecules of condensation type do not exist anymore at higher melt temperature as whole entities, but as truly short sections is well established and accepted. For some unknown reasons, this fact is not considered by the specialists researching the diffusion and mass transfer processes in melts of condensation polymers. Possibly because all studies related with the Reptation concept have been performed with non-condensation polymers, as also demonstrated by a recent review on modeling of entangled polymer diffusion in melts and nanocomposites [124].

754 17 VII.

755 18 Concluding Remarks

Summarizing the above considerations, we could conclude that the diffusion mechanism in polymer melts could be at least of two types. Depending on molecular weight and temperature, or more precisely, dealing with substances with relatively low molecular weights (monomers, oligomers, that is before reaching the molecular weight of the segment) independent kinetic elements are the whole molecules and the diffusion mechanism is the same as that in the melts of low molecular weight substances.

With the further rise of the molecular weight, i. e. above that of the segment, the independent kinetic elements are the segments. Their number in a single macromolecule depends on its flexibility -the higher the flexibility the shorter the segment length and the larger their number is [5]. The diffusion mechanism is segmental to which could be applied the Reptation concept.

Dealing with melts of condensation polymers it should be noted that the outlined two diffusion mechanisms are valid for melt temperatures not much higher than the melting temperatures. With further rise of melt temperature (for example, for PET it is above (T m + 100 o C) very intensive exchange reactions take place, which results in a drastic change of the diffusion mechanism -the independent kinetic elements are not the molecules neither the segments but the repeating units or their small blocks with sizes typical for the molecules of low molecular weight substances. It follows that the diffusion mechanism for this range of temperatures is the same as that for the case of the melts of low molecular weight substances.

172 In conclusion, the diffusion mechanism in polymer melts could be of two types -molecular and segmental. The

Reptation concept can be applied to segmental type of diffusion only. It follows that for melts of condensation polymers at extremely high melt temperatures the "Reptation model" cannot be used for explanation of the diffusion mechanism since independent kinetic elements are the repeating units, that is the mechanism is molecular.

In Figure 12 an attempt is undertaken to present schematically the described situation stressing on the individual kinetic elements and the respective diffusion mechanism in melts. -monomer molecules, -polymer chain comprised of chemically bonded segments, -repeating unit. Diffusion mechanism: Case I -"jump-like" (Frenkel), Case II -"snake-like" (de Gennes), Case III: -as Case I.

Finally, it seems important to mention that the phenomenon taking place in the melts of condensation polymers 781 at extremely high temperatures was analyzed 40 years ago and called "chemically released diffusion" [89]. Some 782 later this approach was supported by Economy et al. [106]. Very recently [53], it was discussed again in relation 783 to chemical peculiarities of condensation polymers, as well as commented by Pigot and Dumur [116] in their 784 review on recent advances of hierarchical and sequential growth of macromolecular organic structures on surface. 785 They state that the concept of chemically released diffusion is more adapted than "self-assembly" to describe 786 the formation of covalent phases on surface, the chemical composition of the polymer under growth continuously 787 evolving by exchange reactions [116]. 788

The dissipation of macromolecules into single repeating units because of proceeding of exchange (trans) reactions in the melts of condensation polymers is well-known and many-fold documented fact ??53-55, 68,69,86,87,89-92,96-98,103-108,110-115,118-122]. Nevertheless, it remains neglected by the researchers studying various processes in polymer melts (flow, diffusion, mass transfer, deformation, and others) as well as their mechanisms. A good example in this respect is the fact that studies on reptation mechanism have been performed exclusively on noncondensation polymers (e.g. [17][18][19][20]).

The role of the independent kinetic entities in melts can be played by the single (small) molecules, by the

segments (in case of macromolecules), and by the chemically non-bonded repeating units (in case of condensation

797 polymers at the highest possible temperatures) as schematically shown in Figure 12. The "Reptation model" can 798 be used for explanation of diffusion mechanism only in cases of segmental type of motion. This means that the

798 be used for explanation of diffusion mechanism only in cases of segmental type of motion. This means that the 799 Reptation concept is not applicable to melts of condensation polymers at highest possible temperatures where the diffusion is realized by the single chemically non-bonded repeating units.



1

Figure 1: Figure 1:



....-O-R"-OOC-R"-CO-:--O-R"-OOCR'-CO-....

two molecules

Figure 4:







Figure 6: Figure 6 :



Figure 7: Figure 7 :



Figure 8: Table 1 :



Figure 9:



Figure 10: Figure 8 :



Figure 11: Figure 9 :



Figure 12:







Figure 13: Figure 10 :

 $^{^1 \}odot$ 2021 Global Journals



Figure 14: Figure 12 :



Figure 15:



Figure 16:

Year 2021 22 (A) Volume Xx XI Issue II V ersion I of Researches in Engineering Global Journal © 2021 Global Journals

Figure 17:

⁸⁰⁰ .1 Year 2021

Again annealing at lower temperatures, or at higher ones (240°C but for shorter times), leads to the formation of two well-defined and spatially separated amorphous phases, characterized by two glass transition temperatures, T g PET and T g PA6 for the PET and PA 6 amorphous phases, respectively (Figure ??c,d). Annealing at 240°C for 5 h (Figure ??e) results in a decrease in the PA 6 amorphous fraction. After annealing for 25 h it disappears completely (Figure ??f). This observation indicates that after such a thermal treatment, all of the amorphous PA 6 is involved in a copolymer with the amorphous PET.

⁸⁰⁷.2 Acknowledgements

The author would like to thank Prof. Dr. H.-J. Radusch for the stimulating discussion on the topic and for his valuable suggestions for improving the manuscript. The author also appreciates The University of Auckland, Department of Mechanical Engineering for hospitality, where this project has been completed. Thanks go also to the Publishers John Wiley & Sons, Inc., Elsevier, Wiley-VCH, for adapting figures with the respective text from their publications (ref. [86] of Wiley, refs. [99] and [100] of Elsevier, and refs. [108] and [110] of Wiley-VCH).

⁸¹³ .3 Global Journal of Researches in Engineering (A) Volume Xx XI Issue ⁸¹⁴ II V ersion I

- 815 [] , 10.1016/j.progpolymsci.2015.06.001. https://doi.org/10.1016/j.progpolymsci.2015.06.001
- 816 [] , 10.1002/macp.1984.021850810. https://doi.org/10.1002/macp.1984.021850810
- 817 [], 10.1002/marc.1990.030110102. https://doi.org/10.1002/marc.1990.030110102
- 818 [], 10.1002/adma.19940060513. https://doi.org/10.1002/adma.19940060513
- 819 [] , 10.1016/0032-3861. 83 p. .
- 820 [] , 10.1002/macp.1996.021970923. https://doi.org/10.1002/macp.1996.021970923
- [1, 10.1016/0032-3861(89)900.
- 822 [Macromolecules ()], doi: 10.1021/ma00144a024. Macromolecules 1985. 18 p. .
- 823 [Macromolecules ()], 10.1021/ma00208a041. https://doi.org/10.1021/ma00208a041 Macromolecules 824 1990. 23 p. .
- 825 [Science ()], doi: 10.1126/science.8171335. Science 1994. 264 p. .
- 826 [© 2021 Global Journals copolyesteramides. Macromolecular Chemistry and Physics ()]
- 10.1002/macp.1996.021970923. https://doi.org/10.1002/macp.1996.021970923 © 2021 Global
 Journals copolyesteramides. Macromolecular Chemistry and Physics 1996. 197 p. .
- [Angewandte Chemie International Edition ()], 10.1002/anie.200904394. Angewandte Chemie International
 Edition 2010. 49 p. .
- ⁸³¹ [Ge et al. ()], T Ge, G S Grest, M Rubinstein. 10.1103/PhysRevLett.120.057801. https://doi.org/10.
- 1103/PhysRevLett.120.057801 Nanorheology of Entangled Polymer Melts. Physical Review Letters 2018.
 120 p. 57801.
- [Materials ()], 10.3390/ma12040662. https://doi.org/10.3390/ma12040662 Materials 2019. 12 p. 662.
- 835 [Voyutskii ()] Autoadhesion and Adhesion of High Polymers, S Voyutskii . 1963. New York: Interscience. p. 272.
- ⁸³⁶ [Awaja ()] 'Autohesion of polymers'. F Awaja . 10.1016/j.polymer.2016.05.043. Polymer 2016. 95 p. .

[Gilmer et al. ()] 'Changes in molecular conformations in poly(ethylene terephthalate) produced by crystallization and drawing as determined by neutron scattering'. J W Gilmer, D Wiswe, H.-G Zachmann, J Kugler
, E W Fischer . 10.1016/0032-3861. https://doi.org/10.1016/0032-3861 Polymer 1986. 27 (86) p.
90039.

- [Yang et al. ()] 'Chemical and Physical Aspects of Self-Healing Materials'. Y Yang , X Ding , M W Urban .
 Progress in Polymer Science 2015. p. .
- [Fakirov and Avramova ()] 'Chemical healing in partially cross-linked polyamides'. S Fakirov , N Avramova .
 10.1002/polb.1987.090250611. Journal of Polymer Science Part B: Polymer Physics 1987. 25 p. .
- [Fakirov ()] 'Chemical healing in poly(ethylene terephthalate)'. S Fakirov . 10.1002/ pol.1984.180221208. Journal
 of Polymer Science: Polymer Physics Edition 1984. 22 p. .
- [Porter and Wang ()] 'Compatibility and transesterification in binary polymer blends'. R S Porter , L H Wang .
 10.1016/0032-3861(92)90866-U. Polymer 2019-2030 (1992. 33.
- [Brown and Szamel ()] 'Computer simulation study of the structure and dynamics of ring polymers'. S Brown ,
- G Szamel . 10.1063/1.477247. https://doi.org/10.1063/1.477247 Journal of Chemical Physics 1998.
 109 p. .

18 CONCLUDING REMARKS

- [Reigh and Yoon ()] 'Concentration dependence of ring polymer conformations from Monte Carlo simulations'.
 S Y Reigh , D Y Yoon . 10.1021/mz300587v. ACS Macro Letters 2013. 2 p. .
- [Fakirov ()] 'Condensation Polymers: Their Chemical Peculiarities Offer Great Opportunities'. S Fakirov
 . 10.1016/j.progpolymsci.2018.09.003. https://doi.org/10.1016/j.progpolymsci.2018.09.003
 Progress in Polymer Science 2019. 89 p. .

[Lenz et al. ()] 'Crystallizationinduced reactions of copolymers: 6. Reorganization of polyesters in the liquid
 crystal state'. R Lenz , J Jin , K Feichtinger . *Polymer* 1983. 24 p. .

[Reis et al. ()] 'Dffusion coefficients in polymer-solvent systems for highly concentrated polymer solutions'. R
 A Reis, J V Oliveira, N Nobrega. 10.1590/S0104-66322001000400003. http://dx.doi.org/10.1590/
 S0104-66322001000400003 Brazilian Journal of Chemical Engineering 2001. 18 p. .

[Mills et al. ()] 'Diffusion of polymer rings in linear polymer matrices'. P J Mills , J W Mayer , E J Kramer
 , G Hadziioannou , P Lutz , C Strazielle , P Rempp , A J Kovacs . 10.1021/ma00169a008. https:
 //doi.org/10.1021/ma00169a008 Macromolecules 1987. 20 p. .

[Muhlebach et al.] Direct evidence for transesterification and randomization in a mixture of homopolyesters of poly
 (4-hydroxybenzoic acid) and poly (6-hydroxy-2-naphthoic acid) above 450 degree, A Muhlebach , J Economy
 R D Johnson , T Karis , J Lyerla .

- [Perkins et al.] Direct observation of tube-line motion of a single polymer-chain, T T Perkins, D E Smith, S
 Chu.
- [Serhatkulu et al. ()] 'Dynamic mechanical study of amorphous phases in poly(ethylene terephthalate)/nylon-6
 blends'. T Serhatkulu , I Bahar , B Erman , S Fakirov , M Evstatiev , D Sapundjieva . 10.1016/0032-3861(95.
 https://doi.org/10.1016/0032-3861(95 Polymer 1995. 36 p. 97335.
- [Klein ()] 'Dynamics of entangled linear, branched, and cyclic polymers'. J Klein . 10.1021/ma00155a018.
 https://doi.org/10.1021/ma00155a018 Macromolecules 1986. 19 p. .
- [Leibler et al. ()] 'Dynamics of telechelic ionomers. Can polymers diffuse large distances without relaxing stress'.
 L Leibler , M Rubinstein , R Colby . ff10.1051/jp2:1993219ff.ffjpa-00247926f. Journal de Physique II 1993. 3
 p. . (EDP Sciences)

 [Rubinstein (ed.) ()] Ed) New Trends in Physics and Physical Chemistry of Polymers, M Rubinstein . 10.1007/978-1-4613-0543-9_35.Year2021. https://doi.org/10.1007/978-1-4613-0543-9_
 35.Year2021 Lee L. H. (ed.) 1989. 1986. Boston, MA: Springer. p. . (Reptation Model of Entangled

- 883 Polymers)
- [Fakirov ()] 'Editorial corner -a personal view: The 'reptation model' and the melts of condensation polymers'.
 S Fakirov . 10.3144/expresspolymlett.2019.25. Express Polymer Letters 2019. 13 p. .
- [Fakirov ()] Effect of temperature on the chemical healing of poly(ethy1ene terephthalate). Die Makromolekulare
 Chemie, S Fakirov . 1984. 185 p. .
- [Calleja et al. ()] 'Effect of transreactions and additional condensation on structure formation and properties of
 condensation polymers'. Balta Calleja, F J Fakirov, S Zachmann, HG. Transreactions in Condensation
 Polymers, (Weinheim) 1999. Wiley-VCH. p. .
- [Xanthos and Warth ()] 'Effects of Transreactions on the Compatibility and Miscibility of Blends of Condensation Polymers'. M Xanthos , H Warth . Transreactions in Condensation Polymers, (Weinheim) 1999.
 Wiley-VCH. p. .

[Abadi et al. ()] 'Entangled polymer dynamics beyond reputation'. M Abadi , M F Serag , S Habuchi .

- 10.1038/s41467-018-07546-7. https://doi.org/10.1038/s41467-018-07546-7 Nature Communica tions 2018. 9 p. 5098.
- [Klein ()] 'Evidence for reptation in an entangled polymer melt'. J Klein . doi: 10. 1038/271143a0. Nature 1978.
 271 p. .
- [Fakirov et al.] S Fakirov, M Sarkissova, Z Denchev. Sequential reordering in condensation copolymers. 3.
 Miscibility-induced sequential reordering in random Year 2021,
- 901 [Fakirov and Evstatievm ()] S S Fakirov , M Evstatievm . Microfibrillar reinforced composites -new materials
 902 from polymer blends, 1994. 6 p. .
- [Fakirov and Ed ()] S Fakirov, Ed. Transreactions in Condensation Polymers, (Weinheim) 1999. Wiley-VCH.
 p. 509.
- 905 [Hillewaere and Du Prez ()] 'Fifteen chemistries for autonomous external self-healing polymers and composites'.
- X Hillewaere , D Du Prez , FE . 10.1016/j.progpolymsci.2015.04.004. https://doi.org/10.1016/j.
 progpolymsci.2015.04.004 Progress in Polymer Science, 2015. p. .

- 908 [Frenkel ()] Y I Frenkel . Kinetic Theory of Liquids, (Oxford) 1946. Clarendon Press.
- 909 [Fakirov ()] Fundamentals of Polymer Science for Engineers, S Fakirov . 2017. Weinheim: Wiley-VCH.
- 910 [Espinosa et al. ()] 'Healable supramolecular polymer solids'. De Espinosa , L M Fiore , G L Weder , C Foster
- 911 , E J Simon , YC . 10.1016/j.progpolymsci.2015.04.003. https://doi.org/10.1016/j.progpolymsci.
 912 2015.04.003 Progress in Polymer Science 49-50, 60-78 Year 2021. 2015.
- 913 [Volynskii and Bakeev ()] 'Healing of Interfacial Surfaces in Polymer Systems'. A L Volynskii , N F Bakeev
- 914 . 10.1134/S0965545X09100071. https://doi.org/10.1134/S0965545X09100071 Polymer Science Ser 915 A 2009. 51 p. .
- 916 [Fakirov ()] 'Heterochemical healing in linear polycondensates'. S Fakirov . http://pascal-francis.inist.
- 917 fr/vibad/index.php?action=getRecordDetail&idt=8552940 Polymer Communications 1985. 26 p. 918 .
- [Hia et al. ()] I Hia , L Vahedi , V Pasbakhsh , P . 10.1080/15583724.2015.1106555. Self-Healing Polymer
 Composites: Prospects, Challenges, and Application, 2016. 56 p. .
- [Economy et al. ()] 'Interchain transesterification reactions in copolyesters'. J Economy , L A Schneggenburger ,
 D Frich . Transreactions in Condensation Polymers, S Fakirov, S (ed.) (Weinheim) 1999. Wiley-VCH. p. .
- [Kricheldorf and Denchev ()] 'Interchange reactions in Condensation Polymers and Their Analysis by NMR
 Spectroscopy'. H R Kricheldorf , Z Denchev . Transreactions in Condensation Polymers, S Fakirov (ed.)
- 925 (Weinheim) 1999. Wiley-VCH. p. .
- Benoit et al. ()] 'Interpretation of neutron scattering results during transesterification reactions'. H C Benoit ,
 E W Fischer , H G Zachmann . *Polymer* 1989. 30 p. .
- [Leibler et al. ()] L Leibler , M Rubinstein , R H Colby . 10.1021/ma00016a034. Dynamics of reversible networks,
 1991. 24 p. .
- [Avramova and Fakirov ()] 'Liquid crystalline polymer laminates'. N Avramova , S Fakirov .
 10.1002/app.1991.070420411. Journal of Applied Polymer Science 1991. 42 p. .
- [Fakirov et al. ()] 'Long spacing in polyblock poly(ether ester) s -origin and peculiarities'. S Fakirov, A Apostolov
 , C Fakirov . 10.1080/00914039208034813. International Journal of Polymeric Materials 1992. 18 p. .
- [Fakirov et al. ()] 'Microfibrillar reinforced composite from drawn poly(ethylene terephthalate)/nylon-6 blend'.
- S Fakirov , M Evstatiev , J M Schultz . 10.1016/0032-3861. https://doi.org/10.1016/0032-3861
 Polymer 1993. 34 (93) p. 90700.
- ⁹³⁷ [Devaux (ed.) ()] Model studies of transreactions in condensation polymers, J Devaux . Fakirov S., (ed.) 1999.
 ⁹³⁸ Weinheim: Wiley-VCH. p. . ((Ed): Transreactions in Condensation Polymers)
- [Karatrantos et al. ()] 'Modeling of Entangled Polymer Diffusion in Melts and Nanocomposites: A Review'.
 A Karatrantos , R J Composto , K I Winey , M Kröger , N Clarke . 10.3390/polym11050876. https: //doi.org/10.3390/polym11050876 Polymers 2019. 11 p. 876.
- Mcalea et al. ()] 'Molecular dimensions in poly(ethylene terephthalate) by small-angle neutron scattering'. K P
 Mcalea , J M Schultz , K H Gardner , G D Wignall . 10.1021/ma00145a025. https://doi.org/10.1021/
 ma00145a025 Macromolecules 1985. 18 p. .
- [Halverson et al. ()] 'Molecular dynamics simulation study of nonconcatenated ring polymers in a melt'. J D
 Halverson , W B Lee , G S Grest , A Y Grosberg , K Kremer . http://hdl.handle.net/11858/
 00-001M-0000-000F-6EC2-D II. Dynamics. Journal of Chemical Physics 2011. 134 p. 204905.
- Bachus and Kimmich ()] 'Molecular weight and temperature dependence of self-diffusion coefficients in polyethylene and polystyrene melts investigated using a modified n.m.r. field-gradient technique'. R Bachus, R Kimmich . 10.1016/0032-3861(83)90146-5. https://doi.org/10.1016/0032-3861(83)90146-5 Polymer
 1983. 24 p. .
- [Yang et al. ()] 'Monte Carlo simulation of a single ring among linear chains: structural and dynamic heterogeneity'. Y B Yang , Z Y Sun , C L Fu , L J An , Z G Wang . 10.1063/1.3466921. Journal of Chemical Physics 2010. 133 p. 64901.
- [Evstatiev et al. ()] 'Morphology of microfibrillar reinforced composites PET/PA 6 blend'. M Evstatiev , N
 Nikolov , S Fakirov . 10.1016/0032-3861(96)00137-1. Polymer 1996. 37 p. .
- ⁹⁵⁷ [Habuchi et al.] Multimode diffusion of ring polymer molecules revealed by a single-molecule study, S Habuchi ,
 ⁹⁵⁸ N Satoh , T Yamamoto , Y Tezuka , M Vacha .
- ⁹⁵⁹ [Fakirov ()] 'Nano-/micrifibrillar polymer-polymer and single polymer composites: The converting instead
 of adding concept'. S Fakirov . 10.1016/j.compscitech.2013.10.007. https://doi.org/10.1016/j.
 ⁹⁶¹ compscitech.2013.10.007 Composites Science and Technology 2013. 89 p. .
- 962 [Ge et al. ()] 'Nanoparticle Motion in Entangled Melts of Linear and Nonconcatenated Ring Polymers'. T Ge ,
- J T Kalathi , J D Halverson , G S Grest , M Rubinstein . 10.1021/acs.macromol.6b02632. Macromolecules
 2017. 50 p. .

- 965 [Keshavarz et al. ()] 'Nanoscale study of polymer dynamics'. M
 Keshavarz , H Hans Engelkamp , J Xu . 10.1021/acsnano.5b
06931. ACS Nano 2016. 10 p. .
- 967 [Youk and Jo ()] 'Origin of miscibility-induced sequential reordering and crystallization-induced sequential
 968 reordering in binary copolyesters: A Monte Carlo simulation'. J H Youk, W H Jo. 10.1002/polb.1106.
 969 Journal of Polymer Science: Part B Polymer Physics 2001. 39 p. .
- [Ricarte et al. ()] 'Phase Separation and Self-Assembly in Vitrimers: Hierarchical Morphology of Molten and
 Semicrystalline Polyethylene/Dioxaborolane Maleimide Systems'. R G Ricarte, F Tournilhac, L Leibler.
 10.1021/acs.macromol.8b02144. Macromolecules 2019. 52 p. .
- 973 [Knigth ()] Plastic: the elephant in the room, S Knigth . April 26/27 (2008. p. . FT Weekend Magazine
- [Kriecheldorf ()] 'Polycondensation: History and New Results'. H Kriecheldorf . Solid State Polycondensation, H
 Kricheldorf, H (ed.) (Berlin) 2014. Springer. p. .
- 976 [Kriecheldorf ()] Polycondensdation: History and New Results, H Kriecheldorf . 2014. Berlin: Springer.
- 977 [Mcleish ()] 'Polymer dynamics: floored by the rings'. T Mcleish . 10.1038/nmat2324. Nature Materials 2008. 7
 978 p. .
- 979 [Rubinstein and Colby ()] *Polymer Physics*, M Rubinstein , R H Colby . 2003. New York: Oxford University 980 Press.
- [Tirrell ()] 'Polymer Self-Diffusion in Entangled Systems'. M Tirrell . 10.5254/1.3536019. https://doi.org/
 10.5254/1.3536019 Rubber Chemistry and Technology 1984. 57 p. .
- [Mcleish ()] 'Polymers without beginning or end'. T Mcleish . DOI: 10.1126/ science.1076810. Science 2005-2006
 (2002. 297.
- 985 [Flory ()] Principles of Polymer Chemistry, P J Flory . 1953. Ithaca NY. p. 88. Cornell University
- [Geyer et al. ()] 'Production, use, and fate of all plastics ever made'. R Geyer , J R Jambeck , K L Law . DOI: 10.1126/ sciadv.1700782. Science Advances 2017. 3 p. e1700782.
- 988 [Scheiner et al. ()] 'Progress Towards Self-Healing Polymers for Composite Structural Applications'. M Scheiner,
- 989 T J Dickens, O I Okoli. 10.1016/j.polymer.2015.11.008. https://doi.org/10.1016/j.polymer.2015.
 990 11.008 Polymer 2015. 83 p. .
- ⁹⁹¹ [Zhong et al. ()] 'Quantifying the impact of molecular defects on polymer network elasticity'. M J Zhong , R
 ⁹⁹² Wang , K Kawamoto , B D Olsen , J A Johnson . 10.1126/science.aag0184[40. Science 2016. 353 p. .
- [Li and Meng ()] Recent Advances in Smart Selfhealing Polymers and Composites, G Li , H Meng . 2015.
 Amsterdam: Elsevier. p. 426.
- Pigot and Dumur] Recent Advances of Hierarchical and Sequential Growth of Macromolecular Organic Structures
 on Surface, C Pigot , F Dumur .
- 997 [Seggern et al. ()] 'Reptation and constraint release in linear polymer melts. An experimental study'. Von Seggern
 998 , J Klotz , S Cantow , H.-J . 10.1021/ma00011a039. Macromolecules 1991. 24 p. .
- [Leger et al. ()] 'Reptation in entangled polymer-solutions by forced Rayleigh light-scattering'. L Leger, H Hervet
 F Rondelez . 10.1021/ma50007a023. Macromolecules 1981. 14 p. .
- [Gennes ()] 'Reptation of a Polymer Chain in the Presence of Fixed Obstacles'. De Gennes , PG .
 1002 10.1063/1.1675789. Journal of Chemical Physics 1971. 55 p. .
- [Kalathi et al. ()] 'Rouse Mode Analysis of Chain Relaxation in Homopolymer Melts'. T Kalathi, S K Kumar, M
 Rubinstein, G S Grest. 10.1039/c5sm00754b. https://doi.org/10.1039/c5sm00754b Macromolecules
 2014. 47 p. .
- [Patton et al. ()] 'Scaling Properties of Branched Polyesters'. E V Patton , J A Wesson , M Rubinstein ,
 J C Wilson , L E Oppenheimer . 10.1021/ma00194a072. https://doi.org/10.1021/ma00194a072
 Macromolecules 1989. 22 p. .
- [Cosgrove et al. ()] 'Self-diffusion and spin-spin relaxation in cyclic and linear polydimethylsiloxane melts'. T
 Cosgrove , P C Griffiths , J Hollingshurst , R D C Richards , J A Semlyen . 10.1016/0032-3861(96.
 https://doi.org/10.1016/0032-3861(96 Macromolecules 1992. 25 p. . (29)
- [Bartels and Crist ()] 'Self-Diffusion Coefficient in Melts of Linear Polymers: Chain Length and Temperature
 Dependence for Hydrogenated Polybutadiene'. C R Bartels , B Crist . 10.1021/ma00142a04. Macromolecules
 1984. 17 p. .
- [Bartels et al. ()] 'Self-Diffusion in Branched Polymer Melts'. C R Bartels , B Crist , Jr , L J Fetters , W W
 Graessley . 10.1021/ma00157a050. https://doi.org/10.1021/ma00157a050 Macromolecules 1986. 19
 p. .
- [Meerwall et al. ()] 'Self-diffusion of linear and cyclic alkanes, measured with pulsed-gradient spin-echo nuclear
 magnetic resonance'. Von Meerwall, E Ozisik, R Mattice, W L Pfister, PM. 10.1063/1.1539044. Journal
 of Chemical Physics 2003. 118 p. .

- 1021 [Wool ()] 'Self-healing materials: a review'. R P Wool . 10.1039/B711716G. https://doi.org/10.1039/
 1022 B711716G Soft Matter 2008. 4 p. .
- [Ghosh and Ed ()] Self-healing Materials: Fundamentals, Design Strategies, and Applications, S K Ghosh , Ed .
 2009. Weinheim: Wiley-VCH. p. 296.
- [Stukalin et al. ()] 'Self-Healing of Unentangled Polymer Networks with Reversible Bonds'. E B Stukalin , L.-H
 Cai , N A Kumar , L Leibler , M Rubinstein . 10.1021/ma. https://doi.org/10.1021/ma Macromolecules
 2013. 46 p. 1111.
- [Mphahlele et al. ()] 'Self-Healing Polymeric Composite Material Design, Failure Analysis and Future Outlook:
 A Review'. K Mphahlele, S S Ray, A Kolesnikov. 10.3390/polym9100535. https://doi.org/10.3390/
 polym9100535 Polymers 2017. 9 (535) p. .
- [Yang and Urban ()] 'Self-healing polymeric materials'. Y Yang , M V Urban . 10.1039/C3CS60109A. https: //doi.org/10.1039/C3CS60109A Chemical Society Reviews 2013. 42 p. .
- [Mauldin and Kessler ()] 'Self-healing polymers and composites'. T C Mauldin , M R Kessler .
 1034 10.1179/095066010X12646898728408. International Materials Reviews 2010. 55 p. .
- [He et al. ()] 'Self-healing polymers and composites for extreme environments'. Y O He , M H Malakooti , A
 Henry , H A Sodano . Journal of Materials Chemistry A 2016. 4 p. .
- [Blaiszik et al. ()] Self-Healing Polymers and Composites. The Annual Review of Materials Research, B J Blaiszik
 , S Kramer , B Olugebefola , S C Moore , J S Sottos , N R White , SR . 10.1146/annurev-matsci-07090910453240. 2010. 2010. 40 p. .
- [Zhang and Rong ()] Self-Healing Polymers and Polymer Composites, M Q Zhang , M Z Rong . 2011. Hoboken,
 NJ: John Wiley & Sons. p. 448.
- [Meerwall et al.] Selfdiffusion in solutions of polystyrene in tetrahydrofuran-comparison of concentration depen dences of the diffusion-coefficients of polymers, Von Meerwall, E D Amis, E J Ferry, JD. (and a ternary
 probe component)
- [Yuan et al. ()] 'Selfhealing in polymers and polymer composites. Concepts, realisation and outlook: A review'.
 Y C Yuan , T Yin , M Z Rong , M Q Zhang . 10.3144/EXPRESSPOLYMLETT.2008.29. Express Polymer
 Letters 2008. 2 p. .
- [Semenov and Rubinstein ()] A N Semenov , M Rubinstein . 10.1007/s100510050155. https://doi.org/10.
 1007/s100510050155 Dynamics of strongly entangled systems: activated reptation, 1998. 1 p. .
- [Denchev et al. ()] 'Sequence length determination in poly(ethylene terephthalate)-bisphenol-A polycarbonate
 random copolymers by application of selective degradation'. Z Denchev , A Duchesne , M Stamm , S Fakirov
 10.1002/(SICI)1097-4628. https://doi.org/10.1002/(SICI)1097-4628 Journal of Applied Polymer
 Science 1998. 19 980418. 68 p. . (3<429::AID-APP10>3.0.CO;2-Q)
- [Fakirov and Denchev ()] 'Sequential reordering in condensation copolymers'. S Fakirov , Z Denchev . Transreactions in Condensation Polymers, S Fakirov (ed.) (Weinheim) 1999. Wiley-VCH. p. .
- [Fakirov et al. ()] 'Sequential reordering in condensation copolymers. 1. Meltingand crystallization-induced
 sequential reordering in immiscible blends of poly(ethylene terephthalate) with polycarbonate or polyarylate'.
 S Fakirov , M Sarkissova , Z Denchev . Macromolecular Chemistry and Physics 1996. 197 p. .
- [Denchev et al. ()] Sequential reordering in condensation copolymers. 2. Melting-and crystallization-induced sequential reordering in miscible poly(butylene terephthalate)/ polyarilate blends. Macromolecular Chemistry and Physics, Z Denchev, S Fakirov, M Sarkissova, F Yilmaz. -10.1002/macp.1996.021970922. 1996. 197 p.
 .
- [Denchev et al. ()] Sequential reordering in condensation polymers, 5. Preparation and characterization of copolymers via transesterification of a polycaprolactone/poly(2,2-dimethyltrimethylene carbonate) blend.
 Macromolecular Chemistry and Physics, Z Denchev, A Bojkova, A Duchesne, H Hoecker, H Keul, S
 Fakirov. 199:10 <2153. 1998. 19981001. 199 p. . (AID-MA CP2153>3.0.CO;2-)
- [Shusharina et al. ()] N P Shusharina, E B Zhulina, A V Dobrynin, M Rubinstein. 10.1021/ma051324g. Scaling
 Theory of Diblock Polyampholyte Solutions, 2005. 38 p. .
- [Abadi et al. ()] 'Single-molecule imaging reveals topology dependent mutual relaxation of polymer chains'. M
 Abadi , M F Serag , S Habuchi . 10.1021/acs.macromol.5b01388. Macromolecules 2015. 48 p. .
- [Adjari et al. ()] 'Slippage of an entangled polymer melt on a grafted surface'. A Adjari , F Brochard-Wyart
 , P.-G De Gennes , L Leibler , J.-L Viovy , M Rubinstein . 10.1016/0378-4371(94)90415-4. https:
 //doi.org/10.1016/0378-4371(94)90415-4 Physica A: Statistical Mechanics and Its Applications
 1074 1994. 204 p. .
- [Fakirov (ed.) ()] Solid State Behavior of Linear Polyesters and Polyamides, S Fakirov. Schultz J. M., Fakirov S.,
 (ed.) 1990. Englewood Cliffs, New Jersey: Prentice Hall. p. . (Solid state reactions in linear polycondensates)

- 1077 [Steinborn-Rogulska and Rokicki ()] 'Solid state polycondensation (SSP) as a method to obtain high molecular
 1078 weight polymers Part 1. Parameters influencing the SSP process'. I Steinborn-Rogulska, G Rokicki .
 1079 10.14314/polimery.2013.003. Polimery 2013. 58 p. .
- [Papaspyridis and Vouyiouka ()] Solid State Polymerization, C D Papaspyridis , S N Vouyiouka . 2009. New
 York: John Wiley & Sons. p. 312.
- [Mendes et al. ()] 'Solid State Polymerization of PET/PC Extruded Blend: Effect of Reaction Temperature on Thermal, Morphological and Viscosity Properties'. L C Mendes, I A Mallet, S P Cestari, F G De Albuquerque Dias . 10.1590/0104-1428.1518. http://dx.doi.org/10.1590/0104-1428.1518 Polímeros 2014. 24 p.
- 1086 [Vouyiouka et al. ()] Solid state polymerization of poly(lactic acid): Some fundamental parameters,
 1087 S N Vouyiouka , P Theodoulou , A Symeonidou , C D Papaspyridis , R Pfaendner .
 1088 10.1016/j.polymdegradstab.2013.06.012. https://doi.org/10.1016/j.polymdegradstab.2013.06.
 1089 012 2013. 13 p. . (Polymer Degradation and Stabilisation)
- [Kasmi et al. ()] 'Solid-State Polymerization of Poly(ethylene furanoate) Biobased Polyester. I. Effect of Catalyst
 Type on Molecular Weight Increase'. N Kasmi , M Majdoub , G Z Papageorgiou , D S Achilias , D N Biliaris
 1032 . 10.3390/polym9110607. Polymers 2017. 9 (607) p. .
- [Robertson and Smith ()] Strong effects of molecular topology on diffusion of entangled DNA molecules, R
 M Robertson , D E Smith . 10.1073/pnas.0700137104. https://doi.org/10.1073/pnas.0700137104
 2007. PNAS. 104 p. .
- 1096 [Carothers ()] 'Studies on polymerization and ring formation'. W H Carothers . 10.1021/ja01383a041. https: 1097 //doi.org/10.1021/ja01383a041 Journal of American Chemical Society 1929. 51 p. .
- [Avramova and Fakirov ()] 'Study of the healing process in native cellulose. Die Makromolekulare Chemie'. N
 Avramova , S Fakirov . *Rapid Communications* 1990. 11 p. .
- [Avramova ()] 'Study of the healing process of polymers with different chemical structure and chain mobility'.
 N Avramova . 10.1016/0032-3861(93)90433-B. https://doi.org/10.1016/0032-3861(93)90433-B
 Polymer 1993. 34 p. .
- [Kugler et al. ()] Study of Transesterification in Poly(ethylene terephthalate) by Small-Angle Neutron Scattering.
 Macro molecules, J Kugler, J W Gilmer, D W Wiswe, H G Zachmann, K Hahn, E W Fischer.
 10.1021/ma00171a041. https://doi.org/10.1021/ma00171a041 1987. 20 p.
- [Fakirov ()] 'The Concept of Micro-or Nanofibrils Reinforced Polymer-Polymer Composites'. S Fakirov . Synthetic
 Polymer-Polymer Composites, D Bhattacharyya, S Fakirov (ed.) (Munich) 2012. Hanser. p. .
- Inos [Droescher and Schmidt ()] 'The kinetics of the ester-interchange reaction of poly(ethylene terephthalate)'. M
 Droescher , F G Schmidt . 10.1007/BF00256315. https://doi.org/10.1007/BF00256315 Polymer
 Bulletin 1981. 4 p. .
- 1111 [Klein ()] 'The self-diffusion of polymers'. J Klein . Contemporary Physics 1979. 20 p. .
- 1112 [Doi and Edwards] The theory of polymer dynamics, M Doi, S F Edwards. Oxford: Oxford Science Publications.
- [Arakawa et al. ()] 'Thermal analysis of drawn nylon 6'. T Arakawa , F Nagatoshi , N Arai .
 10.1002/pol.1968.110060710. https://doi.org/10.1002/pol.1968.110060710 Journal of Polymer
 Science Part C: Polymer Letters 1968. 6 p. .
- [Roovers ()] 'Topological Polymer Chemistry: Progress of Cyclic Polymers'. J Roovers . *Pte. Ltd* Tezuka, Y.
 (ed.) 2013. World Scientific Publishing Co. p. . (Ed) Syntheses, Properties and Functions)
- 1118 [Honda et al. ()] 'Topologydirected control on thermal stability: micelles formed from linear and cyclized 1119 amphiphilic block copolymers'. S Honda , T Yamamoto , Y Tezuka . 10.1021/ja104691j[38. https: 1120 //doi.org/10.1021/ja104691j[38 Journal of American Chemical Society 2010. 132 p. .
- 1121 [Mcleish ()] 'Tube theory of entangled polymer dynamics'. T C B Mcleish . 10.1080/00018730210153216.
 1122 https://doi.org/10.1080/00018730210153216 Advances in Physics 2002. 51 p. .
- [Honda et al. ()] 'Tuneable enhancement of the salt and thermal stability of polymeric micelles by cyclized amphiphiles'. S Honda , T Yamamoto , Y Tezuka . DOI: 10.1038/ ncomms2585. Nature Communication 2013. 4 p. 1574.
- [Kapnistos et al. ()] 'Unexpected power-law stress relaxation of entangled ring polymers'. M Kapnistos , M Lang
 , D Vlassopoulos , W Pyckhout-Hintzen , D Richter , D Cho , T Chang , M Rubinstein . 10.1038/nmat2292.
 https://doi.org/10.1038/nmat2292 Nature Materials 2008. 7 p. .
- 1129 [Pasquino ()] 'Viscosity of ring polymer melts'. R Pasquino . 10.1021/mz400344e. ACS Macro Letters 2013. 2 p. 1130
- 1131 [Wunderlich ()] B Wunderlich . Macromolecular Physics, (New York) 1976. Academic. 2 p. .

[Blackwell and Mccullagh ()] 'X-ray Analysis of Transreactions in Blemds of Thermotropic Copolyesters'. J
Blackwell , C M Mccullagh . *Transreactions in Condensation Polymers*, S Fakirov (ed.) (Weinheim) 1999.
Wiley-VCH. p. .

[Hur et al. ()] 'Y: Chain dynamics of ring and linear polyethylene melts from molecular dynamics simulations'.
K Hur , C Jeong , R G Winkler , N Lacevic , R H Gee , D Yoon . 10.1021/ma102659x. *Macromolecules* 2011.
44 p. .