

Moment Capacity, Cracking Behaviour And Ductile Properties Of Reinforced Concrete Beams Using Steel Slag As A Coarse Aggregate

Dr.Arivalagan. S¹

¹ Dr.M.G.R University

Received: 6 June 2012 Accepted: 30 June 2012 Published: 15 July 2012

Abstract

This research paper outlines the method of preparation, testing procedure and salient results on the eco-friendly concrete that is manufactured using the waste products of steel industries. Results of eight flexural behaviour of Steel slag concrete beams and thier comparison with normal weight concrete (NWC) with reinforcement and without reinforcements are presented and discussed .The concrete is of grade 20 and the reinforced concrete beams of size 150 mm x 150 mm x 900 mm were prepared to study the structural behaviour. Similar grade concrete using NWC were also prepared and reinforced. It has been observed from the experimental investigation of the beams, that the moment capacity of SSRC beams was higher than NWC beams . In addition, the mode of failure observed in SSRC was ductile compared to the brittle failure of NWC beams. Thus, the SSRC beams showed a ductile failure, giving ample warning before failure happened. SSRC beams also exhibited a lot of cracking thus the crack width and crack spacing was small. The other advantage for SSRC beams was deflection. The SSRC beams exhibited higher deflection under constant load until failure, compared to NWC beams that failed in brittle manner without warning.

Index terms— Steel slag reinforced concrete (SSRC), Structural Behaviour, Failure Mode, Ductile Behaviour, crack study.

1 Moment Capacity, Cracking Behaviour And Ductile Properties Of Reinforced Concrete Beams Using Steel Slag As A Coarse Aggregate

Arivalagan. S Abstract -This research paper outlines the method of preparation, testing procedure and salient results on the ecofriendly concrete that is manufactured using the waste products of steel industries. Results of eight flexural behaviour of Steel slag concrete beams and thier comparison with normal weight concrete (NWC) with reinforcement and without reinforcements are presented and discussed .The concrete is of grade 20 and the reinforced concrete beams of size 150 mm x 150 mm x 900 mm were prepared to study the structural behaviour. Similar grade concrete using NWC were also prepared and reinforced. It has been observed from the experimental investigation of the beams, that the moment capacity of SSRC beams was higher than NWC beams . In addition, the mode of failure observed in SSRC was ductile compared to the brittle failure of NWC beams. Thus, the SSRC beams showed a ductile failure, giving ample warning before failure happened. SSRC beams also exhibited a lot of cracking thus the crack width and crack spacing was small. The other advantage for SSRC beams was deflection. The SSRC beams exhibited higher deflection under constant load until failure, compared to NWC beams that failed in brittle manner without warning.

2 Introduction

urrently India has taken a major initiative on developing the infrastructures such as express highways, power projects and industrial structures etc., to meet the requirements of globalization. In the construction of buildings and other structures concrete plays the rightful role and a large quantum of concrete is being utilized. Use of more and more environment-friendly materials and industrial wastes in any industry in general and construction industry in particular, is of paramount importance. A number of studies have been conducted concerning the protection of natural resources, prevention of environmental pollution and contribution to the economy by using the waste material like fly ash and steel slag. This would pose problem for their safe disposal and Sometimes degrades the environment. The structural grade Steel slag concrete produced using Slag is a Author : Post doctoral fellow, Professor and H.o.D Dept. of Civil Engineering Dr.M.G.R Educational and Research Institute, Dr.M.G.R University, Chennai, Tamil Nadu, India. Phone: 9444738687, E-mail : arivu357@yahoo.co.in byproduct of metal smelting in the process of refining metals and making alloys referred to hereafter as SSRC. Slag appears in concrete, aggregate road materials, as ballast, and is sometimes used as a component of phosphate fertilizer. Like other industrial by products, slag actually has many uses, and rarely goes as waste. Ashour (2000) concluded from his investigation the members with a displacement ductility in the range of 3 to 5 has adequate ductility and can be considered for structural member subjected large displacements, such as sudden force caused by earth quake. Delsye et al.(2006) conducted an experiment on light weight concrete beams made with oil palm shell. From their research it was concluded that all the LSC beams are satisfied all the serviceability requirements as per ACI 318 and BIS 8110 codes. Ganesan et al(2007) conducted an experimental programme has been carried out to compare the behaviour of high performance concrete (HPC) and steel fibre reinforced high performance concrete (SFRHPC) flexural members under two point loading. Results indicate that introduction of steel fibres significantly improves the cracking behaviour in terms of significant increase in first crack load and the formation of large number of finer cracks. However, only marginal improvement was observed in the case of ultimate load. Addition of steel fibres to HPC imparted high ductility to structural members which is essential for seismic force resisting structures. Hisham Qasraui et al. (2009) studied the effect of waste material of steel plant in concrete. In their investigation local unprocessed steel slag was used in concrete as fine aggregate replacing the sand partly or totally. The compressive strength of concrete was reported to be improved when steel slag is used for low sand replacement ratio (up to 30%). Johnson Alengaram et al, (2008) conducted experiments on palm kernel shell concrete and its comparison with normal weight concrete (NWC). From their work they conclude that the PKSC beams showed a ductile failure, giving ample warning before failure. PKSC beams also exhibited a lot of cracking thus the crack width and crack spacing were small. The other advantage for C I ebruary F PKSC beams was deflection. The PKSC beams exhibited higher deflection under constant load until failure, compared to NWC beams that failed in brittle manner without warning. Khidhair et al. (2009) has used the steel slag as replacement of aggregate in the concrete. The results showed that the density of concrete, compressive strength, flexural strength after 7 days and 28 days were increased by increasing slag content while water absorption was decreased by increasing slag content. Matsunaga et al. (2003) have prepared SSC with small amount of an alkali activator (calcium hydroxide or lime dust). The compressive strength of these SSC products was reported to exceed 18 N/mm², which is the general design strength of breakwater blocks. It was also reported that the 91 days compressive strength is approximately 1.3 times greater than 28 days strength. Ramakrishnan et al. (1987) studied the flexural fatigue performance of concrete reinforced with collated hooked-end steel fibres of size 50 mm × 0.50 mm and 60 mm × 0.80 mm. Two different fibre volume fractions of 0.50% and 0.75% were tested. After addition of these fibres to the concrete, the ductility and post-crack energy absorption capacity were greatly increased.

3 II.

4 Research Significance

The present investigation was planned to study the performance of SSRC beams containing slags as a coarse aggregate subjected to flexural bending loading. Concrete containing five volume fractions of steel slags of 10%, 20%, 30%, 40% and 50% with steel slag is tested. The flexural bending tests of SSRC were determined for different volume fractions of steel slags and compared with that of plain and reinforced concrete beams.

5 III.

6 MATERIAL PROPERTIES a) Steel Slag-Physical and Chemical Properties

Steel slag aggregates are highly angular in shape and have rough surface texture. They have high bulk specific gravity and moderate water absorption (less than 3 percent) The physical properties of steel slag are shown in Table 1. The chemical composition of slag is usually expressed in terms of simple oxides calculated from elemental analysis determined by X-ray fluorescence. Table 2 lists the range of compounds present in steel slag from a typical base oxygen furnace. Virtually all steel slags fall within these chemical ranges but not all steel slags are suitable as aggregates of more importance is the mineralogical form of the slag, which is highly dependent on the

99 rate of slag cooling in the steel-making process. The cooling rate of steel slag is sufficiently low so that crystalline
100 compounds are generally formed. Free calcium and magnesium oxides are not completely consumed in the steel
101 slag, and there is general agreement that the hydration of unslaked lime and magnesia in contact with moisture
102 is largely responsible for the expansive nature of most steel slags. Steel slag is mildly alkaline, with a solution
103 pH generally in the range of 8 to 10. However, the pH of leachate from steel slag can exceed 11, a level that can
104 be corrosive to aluminum or galvanized steel pipes placed in direct contact with the slag.

105 7 b) Concrete Properties

106 The concrete mix was made with ordinary Portland cement, river sand and coarse aggregate of maximum size
107 20mm. Cement, sand and coarse aggregates was 1:1. from ordinary Portland cement, river sand and coarse
108 aggregates maximum 20mm, and steel fibers were added to the dry mix of the materials. Water was then added
109 to the mix to prepare the concrete. The W/C ratio for the mix was 0.50. After thorough mixing, beam specimens
110 were cast along with companion cube moulds to measure the compressive strength of concrete. All the beams
111 and companion cubes were compacted properly. The beam specimens were stripped from their moulds after 24
112 hours and submerged in water tank for 28 days for curing after casting. Before testing, the beams were coated
113 with whitewash to facilitate the observation of cracking pattern.

114 8 IV. EXPERIMENTAL PROGRAM

115 In the present investigation, tests (Figure ??2) were conducted on ten beam specimens of 150 mmX150 mm X
116 900 mm cast in moulds. Specimens labels are shown in Table ?? according to the volume of steel slag added
117 in to the concrete. The steel slags are added in to 10%-50%. The beams referred as 10% of steel slag as SSRC1
118 respectively. The reinforcement used are 2 Nos. of 12mm diameter bar for all the beams. All the nine beams
119 were tested in a Universal Testing Machine (U.T.M) of capacity 40 tonnes available in the structural Engineering
120 Laboratory of Dr.M.G.R University. During testing, the beams were preloaded with a minimal force of 0.5 kN
121 to allow initiation of the diagauges. The developments of cracks were observed and crack width was measured
122 at the level of tensile reinforcement using a hand-held microscope with sensitivity of 0.02 mm. All strain, crack
123 width and deflection measurements were measured at every load increment. The first crack load was noted
124 immediately after its formation and all the cracks were marked as and when they propagated in the beam. ??.
125 The theoretical design moments (M_{des}) of the beams was predicted using the parabolic rectangular stress block
126 analysis are recommended by IS 456-2000. For slag beams, the ultimate moment obtained from the experiments
127 was approximately 2% to 32% higher compared to predicted values. From the performed tests, it was observed
128 that for steel slag concrete beams, IS 456 can be used to obtain a conservative estimate of the ultimate moment
129 capacity and also adequate load factor against failure. 4 compares the predicted midspan deflection under service
130 moments with the experimental values. The predicted deflection is calculated from load values according to the
131 strength of materials equation, using the formula $\delta = \frac{5Wl^3}{163EI}$ (1)

132 Where, δ = Midspan deflection in mm, W = Load acting on the beam in kN, l = Effective span of the beam
133 in mm and EI = Flexural rigidity in N/mm^2 .

134 It was observed that the deflection obtained from the experiment at the service moments compares reasonably
135 well to the predicted deflection. The modulus of elasticity of concrete very much governed by the stiffness of the
136 coarse aggregate. From the properties in Table 1, it can be seen that steel slag is porous in nature also equal
137 density compacted to granite, which directly influence the stiffness of the aggregate. Due to the equal modulus
138 of elasticity of the steel slag beam when compared to R.C.C beam, the deflection under the service loads is
139 acceptable as the span-deflection ratios ranged between 167 to 291 and are within the allowable limit provided
140 by IS 456. IS 456 recommends an upper limit of span/250 for the deflection in order to satisfy the appearance
141 and safety criteria of a structure.

142 From the load deflection graph it is observed that the beams beam behave similar to conventional R.C.C
143 beams and 10% to 50% steel slag to concrete shows behaviour at the yield point and have further yielded with
144 loads. Particularly the beam specimens with normal concrete have no ductile failure the failing in compression
145 remaining all specimens are failure in shear failure. Hence it is also observed that the grade of concrete and
146 reinforcement ratio and spacing of stirrups have certain effects on the flexural behaviour of reinforced concrete
147 beam. The ductility of reinforced concrete structures is also of paramount importance because any member should
148 be capable of undergoing large deflection at near maximum load carrying capacity, providing ample warning to
149 the imminence of failure. In this study, the displacement ductility was investigated. Table 4 shows the ductility
150 of the tested steel slag concrete beams. The displacement ductility ratio is taken in terms of $\mu = \frac{\delta_u}{\delta_y}$, which
151 is the ratio of ultimate to first yield deflection, where δ_u is the deflection at ultimate moment and δ_y is the
152 deflection when steel yields. In general, a high ductility ratio indicates that a structural member is capable of
153 undergoing large deflections prior to failure. In this investigation it was observed that the steel slag beams have
154 ductility ratio of more than 3 which means relatively good ductility. One of the important factors contributing
155 to the good ductility behaviour of the steel slag beam was toughness and good shock absorbance nature of steel
156 slag aggregate as indicated by the aggregate crushing value and aggregate impact value from Table 1. Ashour
157 (2000) mentioned that the members with a displacement ductility in the range of 3 to 5 has adequate ductility

10 CONCLUSION

158 and can be considered for structural member subjected to large displacements, due to sudden force caused by
159 earthquake.

160 **9 VI.**

161 **10 CONCLUSION**

162 From the experiments conducted, it was generally observed that the investigation of flexural behaviour of steel
163 slag concrete beam gives encouraging results in favor steel slag to be used as coarse aggregate.

164 1. All steel slag concrete beams showed typical structural behaviour in flexure. The overall flexural behavior of
165 SSRC beams used in this study closely resembles that of equivalent beam made with NWC. 2. The experimental
166 ultimate moment gives a conservative estimate for steel slag concrete beams for 7% to 32% of a theoretical
167 ultimate moment. 3. Deflection of steel slag concrete beams calculated using Equation (1) under service loads
168 can be used to give reasonable predictions. The deflection under the service loads for beams were within the
169 allowable limit provided by IS 456(2000). 4. Steel slag beams showed good ductility behaviour.

170 All the beams exhibited considerable amount of deflection, which gives enough warning before failure. 5. The
crack widths at service loads varies from 0.20 mm to 0.45 mm and this was within the maximum allowable limits.



1

Figure 1: Figure 1 :

171

172

1 2 3

¹(E)© 2012 Global Journals Inc. (US)

²© 2012 Global Journals Inc. (US)

³Moment Capacity, Cracking Behaviour And Ductile Properties Of Reinforced Concrete Beams Using Steel Slag As A Coarse Aggregate



2

Figure 2: Figure 2 :



5

Figure 3: FFigure 5 :

1

Figure 4: Table 1 :

2

Figure 5: Table 2 :

Property	Value
Specific Gravity	3.2 -3.6
Unit Weight, kg/m ³	1600-1820
Absorption	up to 3%
Maximum size of aggregate, mm	16.00
Aggregate impact value (%)	8.00
2012 Aggregate crushing value (%)	9.00
Constituent Composition (%)	
CaO	40 -52
SiO ₂	10 -19
FeO	10 -40 (70 -80% FeO, 20 -30% Fe ₂ O ₃)
MnO	5 -8
MgO	5 -10
Al ₂ O ₃	1 -3
P ₂ O ₅	0.5 -1
S	< 0.1
Metallic Fe	0.5 -10

Figure 6:

4

Beam No.	Deflection form experiment δ_{exp} (mm)	Theoretical deflection δ_{the} (mm)	$\delta_{exp} / \delta_{the}$	Span/ δ_{exp}	Displacement Ductility ratio $\delta_{exp} = \delta_u / \delta_{the}$	Mode of failure
NWC	4.50	1.51	2.98	174	3.46	Flexure
SSRC1	5.50	1.63	3.37	167	3.67	Flexure
SSRC2	4.53	1.41	3.21	173	3.11	Flexure
SSRC3	5.72	1.76	3.23	151	3.00	Flexure
SSRC4	4.00	1.35	2.96	291	3.00	Flexure
SSRC5	4.20	1.30	3.23	229	2.80	Flexure
PSCB1	5.50	1.50	3.67	276	2.11	Shear
PSCB2	5.30	1.40	3.78	320	2.00	Shear
PSCB3	4.95	1.25	3.96	267	1.76	Shear
PCCB	4.50	1.20	3.75	162	1.88	Shear

Figure 7: Table 4 :

173 .1 VII. Acknowledgements

174 This is a Post Doctoral Research work of the author. The authors wish to express their gratitude and sincere
175 appreciations to the President, Dr. M.G.R. Educational and Research Institute (Dr. M.G.R Deemed University),
176 Chennai, Tamil Nadu, India for giving research fund and full assistance of this research. The authors are very
177 grateful for the assistance rendered by the Civil Engineering Laboratory & Technical Staff and University students
178 at various stages of this investigation.

179 [Ganesan and Indira ()] 'Behaviour of Steel Fibre Reinforced High Performance Concrete Members under Flex-
180 ure'. N Ganesan , P V Indira , Abraham R . *IE(I) Journal* 2007. 88 p. .

181 [Matsunga ()] 'Development environmental friendly block made from steel slag'. Matsunga . *Concrete Journal*
182 2003. 41 (4) p. .

183 [Alengaram et al. ()] 'Ductility Behaviour of Reinforced Palm Kernel Shell Concrete Beams'. Johnson Alengaram
184 , U , Mohd Zamin Jumaat , Hilmi Mahmud . *European Journal of Scientific Research* 2008. 23 (3) p. .

185 [AshoorS ()] 'Effect of compressive strength and tensile reinforcement of flexural behaviour of high strength
186 concrete beams'. AshoorS . *Engineering Structures*, 2000. 22 p. .

187 [Delsye et al. ()] 'Flexural Behaviour of Reinforced Lightweight Concrete Beams Made with Oil Palm Shell'. C
188 L Delsye , Md , Abdul Mannan , Kurian V John . *OPS* 2006. 4 (3) p. .

189 [Ramakrishnan et al. ()] *Flexural Fatigue Strength of Steel Fiber Reinforced Concrete. Fibre Reinforced Concrete-*
190 *Properties and Applications*, V Ramakrishnan , G Oberling , P Tatnall . SP-105-13. 1987. Detroit: American
191 Concrete Institute. p. .

192 [Hisham ()] 'Use of low CaO unprocessed steel slag in concrete as fine aggregate'. Faissal Q Hisham , Ibrahim .
193 *Construction and Building Materials* 2009. 23 p. .

194 [Khidhair ()] 'Using of Steel Slag in Modification of Concrete properties'. Falak J Khidhair , Mohammed .
195 *Engineering & Technology Journal* 2009. 27 (9) p. .